



(12)

EUROPEAN PATENT APPLICATION

(21) Application number : **91300841.3**

(51) Int. Cl.⁵ : **C10M 159/16, // C10N20:04,
C10N30:04, C10N60:14**

(22) Date of filing : **01.02.91**

(30) Priority : **01.02.90 US 473625**

(43) Date of publication of application :
07.08.91 Bulletin 91/32

(84) Designated Contracting States :
BE DE FR GB IT NL

(71) Applicant : **EXXON CHEMICAL PATENTS INC.**
200 Park Avenue
Florham Park New Jersey 07932 (US)

(72) Inventor : **Song, Won Ryul**
36 Dorset Lane
Short Hills, New Jersey 07078 (US)
Inventor : **Lundberg, Robert Dean**
4 Brian Drive
Bridgewater, New Jersey 08807 (US)
Inventor : **Gutierrez, Antonio**
22 Tar Heels Road
Mercerville, New Jersey 08619 (US)
Inventor : **Kielst, Robert Arthur**
297 Avenue C
Bayonne, New Jersey 07002 (US)

(74) Representative : **Northover, Robert Frank et al**
Exxon Chemical Limited Exxon Chemical
Technology Centre PO Box 1
Abingdon Oxfordshire, OX13 6BB (GB)

(54) **Ethylene alpha-olefin copolymer substituted Mannich base lubricant dispersant additives.**

not de suite
(57) The present invention is directed to oil-soluble lubricating oil additives comprising Mannich Base condensates of ~~an alkyl-substituted hydroxy-aromatic compound~~ with formaldehyde and an amine, wherein the alkyl-moiety of the aromatic compounds is derived from at least one ethylene alpha-olefin copolymer of 300 to 20,000 number average molecular weight, wherein at least about 30% of the polymer's chains contain terminal ethenylidene unsaturation. The Mannich Base condensates of this invention are useful as dispersants.

BACKGROUND OF THE INVENTION

U.S. Patent 3,458,495 relates to oxidation inhibitors and dispersant-detergent oil additives comprising the reaction product of one equivalent of a phosphosulfurized hydrocarbon and about 0.5 to 4 equivalents of an alkylene amino phenol. The phosphosulfurized hydrocarbons are prepared by reacting a terpene, a petroleum fraction or a 500 to 200,000 molecular weight C₂ to C₆ olefin polymer (including polymers of ethylene, propylene, butylene, isobutylene or isoamylene) and from 5 to 40 wt% of a sulfide of phosphorous. The alkylene amino phenol is prepared by a Mannich Base condensation of aldehyde, alkylene polyamine and alkyl phenol.

$$\begin{array}{c}
 \text{H} \\
 | \\
 \text{CH}_2 - [\text{N} - (\text{C}_n\text{H}_{2n})\text{NH}]_m \text{Y}]_x \\
 | \\
 \text{N} - \text{C}_6\text{H}_3(\text{R}')(\text{OH}) - \text{C}(=\text{O}) - \text{CH}_2 - \text{R} \\
 | \\
 \text{C}(=\text{O})
 \end{array}$$

M. B. Bogdanov et al., "Oxidative Thermal Degradation of Alkenyl Succinic Anhydrides", *Neftekhimiya* 13:743-748 (1973) (English translation) relates to a study of the thermal oxidative stability of the reaction products of succinic anhydride with polyisobutylene or ethylene-propylene copolymer. The study concludes with the most stable reaction product which was the reaction product of succinic anhydride and ethylene-propylene

copolymer containing terminal succinic anhydride groups and having the lowest content of double bonds in the polymer chain.

5

SUMMARY OF THE INVENTION

In accordance with one aspect of the present invention, there are provided novel alkylated hydroxy aromatic compounds wherein the alkyl-moiety of the alkyl phenol is derived from at least one terminally unsaturated ethylene alpha-olefin polymer of 300 to 20,000 number average molecular weight, wherein the terminal unsaturation comprises ethenylidene unsaturation. These compounds are formed in surprisingly high conversions based on the starting ethylene alpha-olefin polymer, providing product mixtures in which unreacted ethylene alpha-olefin polymer concentrations are minimized, thereby obtaining processing efficiencies. The alkylated hydroxy aromatic compounds so formed are useful in the preparation of novel Mannich Base dispersants.

In accordance with other aspects of the present invention, an oil-soluble lubricating oil additive is provided which comprises a Mannich Base condensate of an alkyl substituted hydroxy aromatic compound with formaldehyde and an amine, wherein the alkyl-moiety of the aromatic compounds is derived from at least one terminally unsaturated ethylene alpha-olefin copolymer of 300 to 10,000 number average molecular weight, wherein the terminal unsaturation comprises ethenylidene unsaturation.

The process of this invention permits the preparation of novel oil-soluble Mannich Base condensate lubricating oil additives which are simultaneously characterized by a low concentration of unreacted polymer (usually less than about 40 wt.%, e.g., from 5 to 35 wt.%) and by advantageous viscosity properties to permit the additives to be readily handled. In addition, the novel ethylene alpha-olefin polymers substituted Mannich Base condensate additives of this invention can be characterized by VR values (as hereinafter defined) of not greater than about 4.1, thereby providing advantageous viscosity modifying properties to the lubricating oils containing them. The present invention can produce such substituted polymers in a highly concentrated form as substantially halogen free materials, thereby reducing the corrosivity processing difficulties and environmental concerns which are associated with halogen-containing lubricating oil additives.

Further, dispersant materials can be prepared from the substituted polymers of this invention to provide lubricating oil dispersant products having VR' values of not greater than about 4.1 and VR'/VR_i ratios of less than about 1.11 (as such values and ratios are hereinafter defined). Surprisingly, the process of this invention permits the preparation of highly concentrated, substantially halogen-free dispersants from high molecular weight ethylene-alpha-olefin polymers ($\overline{M}_n > 5000$, e.g., 5,500-10,000) of superior viscosity properties.

The materials of the invention are different from the prior art Mannich Base materials because of their effectiveness and their ability to provide enhanced lubricating oil dispersancy, as exhibited by their enhanced sludge and varnish control properties.

DETAILED DESCRIPTION OF THE INVENTION

PREPARATION OF ETHYLENE ALPHA-OLEFIN COPOLYMER

The polymers employed in this invention are polymers of ethylene and at least one alpha-olefin having the formula $H_2C=CHR^1$ wherein R^1 is straight chain or branched chain alkyl radical comprising 1 to 18 carbon atoms and wherein the polymer contains a high degree of terminal ethenylidene unsaturation. Preferably R^1 in the above formula is alkyl of from 1 to 8 carbon atoms, and more preferably is alkyl of from 1 to 2 carbon atoms. Therefore, useful comonomers with ethylene in this invention include propylene, 1-butene, hexene-1, octene-1, 4-methylpentene-1, decene-1, dodecene-1, tridecene-1, tetradecene-1, pentadecene-1, hexadecene-1, heptadecene-1, octadecene-1, nonadecene-1 and mixtures thereof (e.g., mixtures of propylene and 1-butene, and the like).

Exemplary of such polymers are ethylene-propylene copolymers, ethylene-butene-1 copolymers and the like. Preferred polymers are copolymers of ethylene and propylene and ethylene and butene-1.

The molar ethylene content of the polymers employed in this invention is preferably in the range of between about 20 and about 80 percent, and more preferably between about 30 and about 70 percent. When propylene and/or butene-1 are employed as comonomer(s) with ethylene, the ethylene content of such copolymers is most preferably between about 45 and about 65 percent, although higher or lower ethylene contents may be present.

The polymers employed in this invention generally possess a number average molecular weight of from about 300 to about 20,000 (e.g., from about 300 to 10,000), preferably from about 900 to 20,500, more preferably of from about 900 to 10,000 (e.g., from about 700 to about 15,000; most preferably of from about 1500 to about 5,000). The number average molecular weight for such polymers can be determined by several known techniques. A convenient method for such determination is by size exclusion chromatography (also known as

gel permeation chromatography (GPC)) which additionally provides molecular weight distribution information, see W. W. Yau, J.J. Kirkland and D.D. Bly, "Modern Size Exclusion Liquid Chromatography", John Wiley and Sons, New York, 1979.

Consequently, such polymers generally possess an intrinsic viscosity (as measured in tetralin at 135°C) of between about 0.025 and about 0.9 dl/g, preferably of between about 0.05 and about 0.5 dl/g, most preferably of between about 0.075 and about 0.4 dl/g.

The polymers employed in this invention preferably exhibit a degree of crystallinity such that, when grafted, they are essentially amorphous.

The polymers employed in this invention are further characterized in that up to about 95% and more of the polymer chains possess terminal ethenylidene-type unsaturation. Thus, one end of such polymers will be of the formula $\text{POLY-C}(\text{T}^1)=\text{CH}_2$ wherein T^1 is C_1 to C_{18} alkyl, preferably C_1 to C_8 alkyl, and more preferably C_1 to C_2 alkyl, (e.g., methyl or ethyl) and wherein POLY represents the polymer chain. The chain length of the T^1 alkyl group will vary depending on the comonomer(s) selected for use in the polymerization. A minor amount of the polymer chains can contain terminal ethenyl unsaturation, i.e. $\text{POLY-CH}=\text{CH}_2$, and a portion of the polymers can contain internal monounsaturations, e.g. $\text{POLY-CH}=\text{CH}(\text{T}^1)$, wherein T^1 is as defined above.

The polymer employed in this invention comprises polymer chains, at least about 30 percent of which possess terminal ethenylidene unsaturation. Preferably at least about 50 percent, more preferably at least about 60 percent, and most preferably at least about 75 percent (e.g. 75-98%), of such polymer chains exhibit terminal ethenylidene unsaturation. The percentage of polymer chains exhibiting terminal ethenylidene unsaturation may be determined by FTIR spectroscopic analysis, titration, or C^{13}NMR .


The polymer and the composition employed in this invention may be prepared as described in U.S. Patent 4,668,834, in European Patent Publications 128,046, 129,368, and 0260999.

The polymers for use in the present invention can be prepared by polymerizing monomer mixtures comprising ethylene in combination with other monomers such as alpha-olefins having from 3 to 20 carbon atoms (and preferably from 3-4 carbon atoms, i.e., propylene, butene-1, and mixtures thereof) in the presence of a catalyst system comprising at least one metallocene (e.g., a cyclopentadienyl-transition metal compound) and an alumoxane compound. The comonomer content can be controlled through the selection of the metallocene catalyst component and by controlling the partial pressure of the various monomers.


The catalysts employed in the production of the reactant polymers are organometallic coordination compounds which are cyclopentadienyl derivatives of a Group 4b metal of the Periodic Table of the Elements (56th Edition of Handbook of Chemistry and Physics, CRC Press [1975]) and include mono, di and tricyclopentadienyls and their derivatives of the transition metals. Particularly desirable are the metallocenes of a Group 4b metal such as titanium, zirconium, and hafnium. The alumoxanes employed in forming the reaction product with the metallocenes are themselves the reaction products of an aluminum trialkyl with water.

In general, at least one metallocene compound is employed in the formation of the catalyst. As indicated, supra, metallocene is a metal derivative of a cyclopentadiene. The metallocenes usefully employed in accordance with this invention contain at least one cyclopentadiene ring. The metal is selected from the Group 4b preferably titanium, zirconium, and hafnium, and most preferably hafnium and zirconium. The cyclopentadienyl ring can be unsubstituted or contain one or more substituents (e.g., from 1 to 5 substituents) such as, for example, a hydrocarbyl substituent (e.g., up to 5 C_1 to C_5 hydrocarbyl substituents) or other substituents, e.g. such as, for example, a trialkyl silyl substituent. The metallocene can contain one, two, or three cyclopentadienyl rings; however, two rings are preferred.

Useful metallocenes can be represented by the general formulas:



wherein Cp is a cyclopentadienyl ring, M is a Group 4b transition metal, R is a hydrocarbyl group or hydrocarboxy group having from 1 to 20 carbon atoms, X is a halogen, and m is a whole number from 1 to 3, n is a whole number from 0 to 3, and q is a whole number from 0 to 3.



wherein $(\text{C}_5\text{R}'_1)$ is a cyclopentadienyl or substituted cyclopentadienyl, each R' is the same or different and is hydrogen or a hydrocarbyl radical such as alkyl, alkenyl, aryl, alkylaryl, or arylalkyl radical containing from 1 to 20 carbon atoms, a silicon containing hydrocarbyl radical, or hydrocarbyl radicals wherein two carbon atoms are joined together to form a C_4 - C_6 ring, R'' is a C_1 - C_4 alkylene radical, a dialkyl germanium or silicon, or a alkyl phosphine or amine radical bridging two $(\text{C}_5\text{R}'_1)$ rings, Q is a hydrocarbyl radical such as aryl, alkyl, alkenyl, alkylaryl, or aryl alkyl radical having from 1-20 carbon atoms, hydrocarboxy radical having from 1-20 carbon atoms or halogen and can be the same or different from each other, Q' is an alkylidene radical having from 1 to about 20 carbon atoms, s is 0 or 1, g is 0, 1 or 2, s is 0 when g is 0, k is 4 when s is 1, and k is 5 when s is 0, and M is as defined above. Exemplary hydrocarbyl radicals are methyl, ethyl, propyl, butyl, amyl, isoamyl,

hexyl, isobutyl, heptyl, octyl, nonyl, decyl, cetyl, 2-ethylhexyl, phenyl and the like. Exemplary silicon containing hydrocarbyl radicals are trimethylsilyl, triethylsilyl and triphenylsilyl. Exemplary halogen atoms include chlorine, bromine, fluorine and iodine and of these halogen atoms, chlorine is preferred. Exemplary hydrocarboxy radicals are methoxy ethoxy, butoxy, amyloxy and the like. Exemplary of the alkylidene radicals is methylenedene, thyliden and propylidene.

Illustrative, but non-limiting examples of the metallocenes represented by formula I are dialkyl metallocenes such as bis(cyclopentadienyl)titanium dimethyl, bis(cyclopentadienyl)titanium diphenyl, bis(cyclopentadienyl)zirconium dimethyl, bis(cyclopentadienyl)zirconium diphenyl, bis(cyclopentadienyl)hafnium dimethyl and diphenyl, bis(cyclopentadienyl)titanium di-neopentyl, bis(cyclopentadienyl)zirconium di-neopentyl, bis(cyclopentadienyl)titanium dibenzyl, bis(cyclopentadienyl)zirconium dibenzyl, bis(cyclopentadienyl)vanadium dimethyl; the mono alkyl metallocenes such as bis(cyclopentadienyl)titanium methyl chloride, bis(cyclopentadienyl)titanium ethyl chloride bis(cyclopentadienyl)titanium phenyl chloride, bis(cyclopentadienyl)zirconium hydrochloride, bis(cyclopentadienyl)zirconium methyl chloride, bis(cyclopentadienyl)zirconium ethyl chloride, bis(cyclopentadienyl)zirconium phenyl chloride, bis(cyclopentadienyl)titanium methyl bromide, bis(cyclopentadienyl)titanium methyl iodide, bis(cyclopentadienyl)titanium ethyl bromide, bis(cyclopentadienyl)titanium ethyl iodide, bis(cyclopentadienyl)titanium phenyl bromide, bis(cyclopentadienyl)titanium phenyl iodide, bis(cyclopentadienyl)zirconium methyl iodide, bis(cyclopentadienyl)zirconium ethyl bromide, bis(cyclopentadienyl)zirconium ethyl iodide, bis(cyclopentadienyl)zirconium phenyl bromide, bis(cyclopentadienyl)zirconium phenyl iodide; the trialkyl metallocenes such as cyclopentadienyltitanium trimethyl, cyclopentadienyl zirconium triphenyl, and cyclopentadienyl zirconium trineopentyl, cyclopentadienylzirconium trimethyl, cyclopentadienylhafnium triphenyl, cyclopentadienylhafnium trineopentyl, and cyclopentadienylhafnium trimethyl.

Illustrative, but non-limiting examples of II and III metallocenes which can be usefully employed are monocyclopentadienyl titanocenes such as, pentamethylcyclopentadienyl titanium trichloride, pentamethylcyclopentadienyl titanium trichloride, bis(pentamethylcyclopentadienyl) titanium diphenyl, the carbene represented by the formula bis(cyclopentadienyl)titanium=CH₂ and derivatives of this reagent such as bis(cyclopentadienyl)Ti=CH₂.Al(CH₃)₃, (Cp₂TiCH₂)₂, Cp₂TiCH₂CH(CH₃)CH₂, Cp₂Ti-CH₂CH₂CH₂; substituted bis(Cp)Ti(IV) compounds such as bis(indenyl) titanium diphenyl or dichloride, bis(methylcyclopentadienyl)titanium diphenyl or dihalides; dialkyl, trialkyl, tetra-alkyl and penta-alkyl cyclopentadienyl titanium compounds such as bis(1,2-dimethylcyclopentadienyl)titanium diphenyl or dichloride, bis(1,2-diethylcyclopentadienyl)titanium diphenyl or dichloride and other dihalide complexes; silicon, phosphine, amine or carbon bridged cyclopentadiene complexes, such as dimethylsilyldicyclopentadienyl titanium diphenyl or dichloride, methyl phosphine dicyclopentadienyl titanium diphenyl or dichloride, methylenedicyclopentadienyl titanium diphenyl or dichloride and other complexes described by formulae II and III.

Illustrative but non-limiting examples of the zirconocenes of Formula II and III which can be usefully employed are, pentamethylcyclopentadienyl zirconium trichloride, pentamethylcyclopentadienyl zirconium trichloride, the alkyl substituted cyclopentadienes, such as bis(ethylcyclopentadienyl)zirconium dimethyl, bis(beta-phenylpropylcyclopentadienyl)zirconium dimethyl, bis(methylcyclopentadienyl)zirconium dimethyl, bis(n-butylcyclopentadienyl)zirconium dimethyl bis(cyclohexylmethylcyclopentadienyl)zirconium dimethyl bis(n-octyl-cyclopentadienyl)zirconium dimethyl, and haloalkyl and dihydride, and dihalide complexes of the above; dialkyl, trialkyl, tetra-alkyl, and penta-alkyl cyclopentadienes, such as bis(pentamethylcyclopentadienyl)zirconium diphenyl, bis(pentamethylcyclopentadienyl)zirconium dimethyl, bis(1,2-dimethylcyclopentadienyl)zirconium dimethyl and mono and dihalide and hydride complexes of the above; silicon, phosphorus, and carbon bridged cyclopentadiene complexes such as dimethylsilyldicyclopentadienyl zirconium dimethyl, methyl halide or dihalide, and methylene dicyclopentadienyl zirconium dimethyl, methyl halide, or dihalide. Mono, di and tri-silyl substituted cyclopentadienyl compounds such as bis(trimethylsilylcyclopentadienyl)zirconium dichloride and dimethyl bis(1,3-di-trimethylsilylcyclopentadienyl)zirconium dichloride and dimethyl and bis(1,2,4-tri-trimethylsilylcyclopentadienyl) zirconium dichloride and dimethyl. Carbenes represented by the formulae Cp₂Zr=CH₂P(C₆H₅)₂CH₃, and derivatives of these compounds such as Cp₂ZrCH₂CH(CH₃)CH₂.

Mixed cyclopentadienyl metallocene compounds such as cyclopentadienyl (pentamethyl cyclopentadienyl)zirconium dichloride, (1,3-di-trimethylsilylcyclopentadienyl) (pentamethylcyclopentadienyl) zirconium dichloride, and cyclopentadienyl(indenyl) zirconium dichloride can be employed.

Most preferably, the polymers used in this invention are substantially free of ethylene homopolymer.

Bis(cyclopentadienyl)hafnium dichloride, bis(cyclopentadienyl)hafnium; dimethyl, bis(cyclopentadienyl)vanadium dichloride and the like are illustrative of other metallocenes.

Some preferred metallocenes are bis(cyclopentadienyl)zirconium; dimethyl, bis(cyclopentadienyl)zirconium dichloride; bis(cyclopentadienyl)titanium dichloride; bis(methylcyclopentadienyl) zirconium dichloride; bis(methylcyclopentadienyl)titanium dichloride; bis(n-butylcyclopentadienyl)zirconium dichloride;

dimethylsilyldicyclopentadienyl zirconium dichloride; bis(trimethylsilylcyclopentadienyl)zirconium dichloride; and dimethylsilyldicyclopentadienyl titanium dichloride; bis(indenyl)zirconium dichloride; bis(4,5,6,7-tetrahydroindenyl)zirconium dichloride; the racemic and/or meso isomer of 1,2-ethylene-bridged bis(4,5,6,7-tetrahydroindenyl)zirconium dichloride; the racemic and/or meso isomer of 1,1-dimethylsilyl-bridged bis(4,5,6,7-tetrahydroindenyl)zirconium dichloride; and the racemic and/or meso isomer of 1,1-dimethylsilyl-bridged bis(methylcyclopentadienyl)zirconium dichloride.

The alumoxane compounds useful in the polymerization process may be cyclic or linear. Cyclic alumoxanes may be represented by the general formula $(R-Al-O)_n$, while linear alumoxanes may be represented by the general formula $R(R'-Al-O)_nR'$. In the general formula R is a C_1 - C_6 alkyl group such as, for example, methyl, ethyl, propyl, butyl and pentyl, n is an integer of from 3 to 20, and n' is an integer from 1 to about 20. Preferably, R is methyl and n and n' are 4-18. Generally, in the preparation of alumoxanes from, for example, aluminum trimethyl and water, a mixture of the linear and cyclic compounds is obtained.

The alumoxane can be prepared in various ways. Preferably, they are prepared by contacting water with a solution of aluminum trialkyl, such as, for examples, aluminum trimethyl, in a suitable organic solvent such as toluene or an aliphatic hydrocarbon. For example, the aluminum alkyl is treated with water in the form of a moist solvent. In an alternative method, the aluminum alkyl such as aluminum trimethyl can be desirably contacted with a hydrated salt such as hydrated copper sulfate or ferrous sulfate. Preferably, the alumoxane is prepared in the presence of a hydrated ferrous sulfate. The method comprises treating a dilute solution of aluminum trimethyl in, for example, toluene, with ferrous sulfate represented by the general formula $FeSO_4 \cdot 7H_2O$. The ratio of ferrous sulfate to aluminum trimethyl is desirably about 1 mole of ferrous sulfate for 6 to 7 moles of aluminum trimethyl. The reaction is evidenced by the evolution of methane.

The mole ratio of aluminum in the alumoxane to total metal in the metallocenes which can be usefully employed can be in the range of about 0.5 : 1 to about 1000 : 1, and desirably about 1 : 1 to about 100 : 1. Preferably, the mole ratio will be in the range of 50 : 1 to about 5 : 1 and most preferably 20 : 1 to 5 : 1.

The solvents used in the preparation of the catalyst system are inert hydrocarbons, in particular a hydrocarbon that is inert with respect to the catalyst system. Such solvents are well known and include, for example, isobutane, butane, pentane, hexane, heptane, octane, cyclohexane, methylcyclohexane, toluene, xylene and the like.

Polymerization is generally conducted at temperatures ranging between about 20° and about 300°C, preferably between about 30° and about 200°C. Reaction time is not critical and may vary from several hours or more to several minutes or less, depending upon factors such as reaction temperature, the monomers to be copolymerized, and the like. One of ordinary skill in the art may readily obtain the optimum reaction time for a given set of reaction parameters by routine experimentation.

The catalyst systems described herein are suitable for the polymerization of olefins in solution over a wide range of pressures. Preferably, the polymerization will be completed at a pressure of from about 10 to about 3,000 bar, and generally at a pressure within the range from about 40 bar to about 2,000 bar, and most preferably, the polymerization will be completed at a pressure within the range from about 50 bar to about 1,500 bar.

After polymerization and, optionally, deactivation of the catalyst (e.g., by conventional techniques such as contacting the polymerization reaction medium with water or an alcohol, such as methanol, propanol, isopropanol, etc., or cooling or flashing the medium to terminate the polymerization reaction), the product polymer can be recovered by processes well known in the art. Any excess reactants may be flashed off from the polymer.

The polymerization may be conducted employing liquid monomer, such as liquid propylene, or mixtures of liquid monomers (such as mixtures of liquid propylene and 1-butene), as the reaction medium. Alternatively, polymerization may be accomplished in the presence of a hydrocarbon inert to the polymerization such as butane, pentane, isopentane, hexane, isooctane, decane, toluene, xylene, and the like.

In those situations wherein the molecular weight of the polymer product that would be produced at a given set of operating conditions is higher than desired, any of the techniques known in the prior art for control of molecular weight, such as the use of hydrogen and/or polymerization temperature control, may be used in the process of this invention. If so desired, the polymerization may be carried out in the presence of hydrogen to lower the polymer molecular weight. Care should be taken to assure that terminal ethenylidene unsaturation is not reduced to less than about 30 percent of the polymer chains.

However, the polymers are preferably formed in the substantial absence of added H_2 gas, that is, the absence of H_2 gas added in amounts effective to substantially reduce the polymer molecular weight. More preferably, the polymerizations will be conducted employing less than 5 wppm, and more preferably less than 1 wppm, of added H_2 gas, based on the moles of the ethylene monomer charged to the polymerization zone.


When carrying out the polymerization in a batch-type fashion, the reaction diluent (if any), ethylene and alpha-olefin comonomer(s) are charged at appropriate ratios to a suitable reactor. Care must be taken that all

ingredients are dry, with the reactants typically being passed through molecular sieves or other drying means prior to their introduction into the reactor. Subsequently, either the catalyst and then the cocatalyst, or first the cocatalyst and then the catalyst are introduced while agitating the reaction mixture, thereby causing polymerization to commence. Alternatively, the catalyst and cocatalyst may be premixed in a solvent and then charged to the reactor. As polymer is being formed, additional monomers may be added to the reactor. Upon completion of the reaction, unreacted monomer and solvent are either flashed or distilled off, if necessary by vacuum, and the low molecular weight copolymer withdrawn from the reactor.


The polymerization may be conducted in a continuous manner by simultaneously feeding the reaction diluent (if employed), monomers, catalyst and cocatalyst to a reactor and withdrawing solvent, unreacted monomer and polymer from the reactor so as to allow a residence time of ingredients long enough for forming polymer of the desired molecular weight and separating the polymer from the reaction mixture.

15 HYDROXYAROMATIC COMPOUNDS

The hydroxy aromatic compounds useful in the preparation of the alkylated materials of this invention include those compounds having the formula (IIIa) :



wherein Ar represents



wherein a is 1 or 2, R' is a halogen radical such as the bromide or chloride radical, b is an integer from 0 to 2, and c is an integer from 1 to 2.

Illustrative of such Ar groups are phenylene, biphenylene, naphthylene and the like.

PREPARATION OF THE ALKYLATED HYDROXYAROMATIC COMPOUNDS

The selected ethylene alpha-olefin polymer and hydroxy aromatic compound are contacted in the presence of a catalytically effective amount of at least one acidic alkylation catalyst under conditions effective to alkylate the aromatic group of the hydroxy aromatic compound. The alkylation catalyst is conventional and can comprise inorganic acids such as H_3PO_4 , H_2SO_4 , HF, BF_3 , HF-BF_3 and the like. The acid catalyst can also comprise an acidic ion exchange resin having acidic groups adsorbed or absorbed thereon, such as Amberlyst 15 resin (Rohm & Haas Co.), and the like. Also useful as catalysts are preformed complexes (or complexes formed in situ) of the foregoing with C_2 to C_{10} ethers, C_1 to C_{10} alcohols, C_2 to C_{10} ketones, phenols and the like, such as BF_3 complexed with dimethyl ether, diethyl ether, phenol, and the like.

The hydroxy aromatic compound and polymer will be generally contacted in a ratio of from about 0.1 to 10, preferably from about 1 to 7, more preferably from about 2 to 5, moles of the aromatic compound per mole of the polymer. The selected acid catalyst can be employed in widely varying concentrations. Generally, when the acid catalyst comprises an inorganic catalyst, the acid catalyst will be charged to provide at least about 0.001, preferably from about 0.01 to 0.5, more preferably from about 0.1 to 0.3, moles of catalyst per mole of hydroxy aromatic compound charged to the alkylation reaction zone. Use of greater than 1 mole of the inorganic catalyst per mole of hydroxy aromatic compound is not generally required. When the acid catalyst comprises a supported catalyst, such as an acidic ion exchange resin, the reactants can be contacted with the ion exchange resin employing any conventional solid-liquid contacting techniques, such as by passing the reactants through the resin (e.g., in a catalyst bed or through a membrane impregnated or otherwise containing the resin catalyst) and the upper limit on the moles of catalyst employed per mole of hydroxy aromatic compound is not critical.

The temperature for alkylation can also vary widely, and will usually range from about 20 to 250°C, preferably from about 30 to 150°C, more preferably from about 50 to 80°C.

The alkylation reaction time can vary and will generally be from about 1 to 5 hours, although longer or shorter times can also be employed. The alkylation process can be practiced in a batchwise, continuous or semi-continuous manner. Preferably, the acid catalyst is neutralized and/or removed prior to contacting the alkylation product mixture with the nucleophilic reagent (e.g., polyamine) and aldehyde reactant. The neutralization can

be accomplished by contacting the crude alkylation product with gaseous ammonia or other basically reacting compound (e.g., aqueous NaOH, KOH, and the like), followed by filtration to remove any precipitated neutralized catalyst solids.

Alkylation processes of the above types are known and are described, for example, in U.S. Patents 3,539,633 and 3,649,229, the disclosures of which are hereby incorporated by reference.

The % conversion obtained in the alkylation according to the present invention is unexpectedly high and conversions of up to 98% and more can be achieved. Generally, the conversions will be at least about 70%, e.g., from 70 to 98%, and preferably from 80 to 95%, based on the percentage of the ethylene alpha-olefin polymer charged which reacts. The precise conversion obtained will depend on the \bar{M}_n of the polymer, the alkylation temperature, reaction time and other factors, and conversions will generally decrease somewhat as polymer \bar{M}_n increases. The alkylation process of this invention is particularly beneficial for polymers having \bar{M}_n of from about 300 to 5,000, preferably 300 to 3,000.

It will be understood that the ethylene alpha-olefin polymers of this invention which are charged to the alkylation reaction zone can be charged alone or together with (e.g., in admixture with) other polyalkenes polyalkenes derived alkenes having from 1 to 20 carbon atoms (butene, pentene, octene, decene, dodecene, tetradecene and the like) and homopolymers of C_3 to C_{10} , e.g., C_2 to C_5 , monoolefins, and copolymers of C_2 to C_{10} , e.g., C_2 to C_6 , monoolefins, said additional polymer having a number average molecular weight of at least about 900, and a molecular weight distribution of less than about 4.0, preferably less than about 3.0 (e.g., from 1.2 to 2.8). Preferred such additional olefin polymers comprise a major molar amount of C_2 to C_{10} , e.g., C_2 to C_6 monoolefin. Such olefins include ethylene, propylene, butylene, isobutylene, pentene, octene-1, styrene, etc. Exemplary of the additionally charged homopolymers is polypropylene, polyisobutylene, and poly-n-butene the like as well as interpolymers of two or more of such olefins such as copolymers of: ethylene and propylene (prepared by conventional methods other than as described above for the preferred ethylene alpha-olefin copolymers employed in this invention, that is, ethylene-propylene copolymers which are substantially saturated, wherein less than about 10 wt% of the polymer chains contain ethylenic unsaturation); butylene and isobutylene; propylene and isobutylene; etc. Other copolymers include those in which a minor molar amount of the copolymer monomers, e.g., 1 to 10 mole %, is a C_4 to C_{18} non-conjugated diolefin, e.g., a copolymer of isobutylene and butadiene; or a copolymer of ethylene, propylene and 1,4-hexadiene; etc. The additional such olefin polymers charged to the alkylation reaction will usually have number average molecular weights of at least about 900, more generally within the range of about 1200 and about 5,000, more usually between about 1500 and about 4000. Particularly useful such additional olefin polymers have number average molecular weights within the range of about 1500 and about 3000 with approximately one double bond per chain. An especially useful additional such polymer is polyisobutylene. Preferred are mixtures of such polyisobutylene with ethylene-propylene copolymers wherein at least 30 wt% of the copolymer chains contain terminal ethenylene monounsaturations as described above.


The number average molecular weight for such polymers can be determined by several known techniques. A convenient method for such determination is by gel permeation chromatography (GPC) which additionally provides molecular weight distribution information, see W. W. Yau, J. J. Kirkland and D. D. Bly, "Modern Size Exclusion Liquid Chromatography", John Wiley and Sons, New York, 1979.

THE ALDEHYDE MATERIAL


The aldehyde reactants will generally comprise formaldehyde or paraformaldehyde, although it will be understood that other aldehyde-group containing compounds, such as C_2 to C_{10} hydrocarbyl aldehydes (e.g., butyraldehyde, acetaldehyde, propionaldehyde, and the like) can also be employed. A preferred group of aldehyde materials are compounds of the formula: R^*CHO , wherein R^* is H or aliphatic hydrocarbon radical having from 1 to 4 carbon atoms.

AMINE COMPOUNDS

Amine compounds useful as nucleophilic reactants for reaction with the selected ethylene-alpha-olefin polymer and aldehyde materials include mono- and (preferably) polyamines, of about 2 to 60, preferably 2 to 40 (e.g. 3 to 20), total carbon atoms and about 1 to 12, preferably 3 to 12, and most preferably 3 to 9 nitrogen atoms in the molecule. These amines may be hydrocarbyl amines or may be hydrocarbyl amines including other groups, e.g., hydroxy groups, alkoxy groups, amid groups, nitriles, imidazoline groups, and the like. Hydroxy amines with 1 to 6 hydroxy groups, preferably 1 to 3 hydroxy groups are particularly useful. Preferred amines are aliphatic saturated amines, including those of the general formulas:




wherein R, R', R'' and R''' are independently selected from the group consisting of hydrogen; C₁ to C₂₅ straight or branched chain alkyl radicals; C₁ to C₁₂ alkoxy C₂ to C₆ alkylene radicals; C₂ to C₁₂ hydroxy amino alkylene radicals; and C₁ to C₁₂ alkylamino C₂ to C₆ alkylene radicals; and wherein R''' can additionally comprise a moiety of the formula:



wherein R' is as defined above, and wherein r and r' can be the same or a different number of from 2 to 6, preferably 2 to 4; and t and t' can be the same or different and are numbers of from 0 to 10, preferably 2 to 7, and most preferably about 3 to 7, with the proviso that the sum of t and t' is not greater than 15. To assure a facile reaction, it is preferred that R, R', R'', R''', r, r', t and t' be selected in a manner sufficient to provide the compounds of Formulas IV and V with typically at least one primary or secondary amine group, preferably at least two primary or secondary amine groups. This can be achieved by selecting at least one of said R, R', R'' or R''' groups to be hydrogen or by letting t in Formula V be at least one when R''' is H or when the VI moiety possesses a secondary amino group. The most preferred amine of the above formulas are represented by Formula V and contain at least two primary amine groups and at least one, and preferably at least three, secondary amine groups.

Non-limiting examples of suitable amine compounds include: 1,2-diaminoethane; 1,3-diaminopropane; 1,4-diaminobutane; 1,6-diaminohexane; polyethylene amines such as diethylene triamine; triethylene tetramine; tetraethylene pentamine; polypropylene amines such as 1,2-propylene diamine; di-(1,2-propylene) triamine; di-(1,3-propylene) triamine; N,N-dimethyl-1,3-diaminopropane; N,N-di-(2-aminoethyl) ethylene diamine; N,N-di(2-hydroxyethyl)-1,3-propylene diamine; 3-dodecyloxypropylamine; N-dodecyl-1,3-propane diamine; tris hydroxyethylaminomethane (THAM); diisopropanol amine; diethanol amine; triethanol amine; mono-, di-, and tri-tallow amines; amino morpholines such as N-(3-aminopropyl)morpholine; and mixtures thereof.

Other useful amine compounds include: alicyclic diamines such as 1,4-di(aminomethyl) cyclohexane, and heterocyclic nitrogen compounds such as imidazolines, and N-aminoalkyl piperazines of the general formula (VII):




wherein p₁ and p₂ are the same or different and are each integers of from 1 to 4, and n₁, n₂ and n₃ are the same or different and are each integers of from 1 to 3. Non-limiting examples of such amines include 2-pentadecyl imidazoline; N-(2-aminoethyl) piperazine; etc.


Commercial mixtures of amine compounds may advantageously be used. For example, one process for preparing alkylene amines involves the reaction of an alkylene dihalide (such as ethylene dichloride or propylene dichloride) with ammonia, which results in a complex mixture of alkylene amines wherein pairs of nitrogens are joined by alkylene groups, forming such compounds as diethylene triamine, triethylenetetramine, tetraethylene pentamine and isomeric piperazines. Low cost poly(ethyleneamines) compounds averaging

about 5 to 7 nitrogen atoms per molecule are available commercially under trade names such as "Polyamin H", "Polyamine 400", "Dow Polyamine E-100", etc.

Useful amines also include polyoxyalkylene polyamines such as those of the formula (VIII) :




where m has a value of about 3 to 70 and preferably 10 to 35 ; and the formula (IX) :



where n''' has a value of about 1 to 40 with the provision that the sum of all the n''' values is from about 3 to about 70 and preferably from about 6 to about 35, and R^4 is a polyvalent saturated hydrocarbon radical of up to ten carbon atoms wherein the number of substituents on the R^4 group is represented by the value of "a", which is a number of from 3 to 6. The alkylene groups in either formula (VIII) or (IX) may be straight or branched chains containing about 2 to 7, and preferably about 2 to 4 carbon atoms.

The polyoxyalkylene polyamines of formulas (VIII) or (IX) above, preferably polyoxyalkylene diamines and polyoxyalkylene triamines, may have average molecular weights ranging from about 200 to about 4000 and preferably from about 400 to about 2000. The preferred polyoxyalkylene polyoxyalkylene polyamines include the polyoxyethylene and polyoxypropylene diamines and the polyoxypropylene triamines having average molecular weights ranging from about 200 to 2000. The polyoxyalkylene polyamines are commercially available and may be obtained, for example, from the Jefferson Chemical Company, Inc. under the trade name "J f-amines D-230, D-400, D-1000, D-2000, T-403", etc.

A particularly useful class of amines are the polyamido and related amines disclosed in U.S. Patent 4,857,217 (the disclosure of which is hereby incorporated by reference in its entirety) which comprise reaction products of a polyamine and an alpha, beta unsaturated compound of the formula :




wherein X is sulfur or oxygen, Y is $-\text{OR}^8$, $-\text{SR}^8$, or $-\text{NR}^8$ (R^9), and R^5 , R^6 , R^7 , R^8 and R^9 are the same or different and are hydrogen or substituted or unsubstituted hydrocarbyl. Any polyamine, whether aliphatic, cycloaliphatic, aromatic, heterocyclic, etc., can be employed provided it is capable of adding across the acrylic double bond and amidifying with for example the carbonyl group ($-\text{C}(\text{O})-$) of the acrylate-type compound of formula X, or with the thiocarbonyl group ($-\text{C}(\text{S})-$) of the thioacrylate-type compound of formula X.

When R^5 , R^6 , R^7 , R^8 or R^9 in Formula X are hydrocarbyl, these groups can comprise alkyl, cycloalkyl, aryl, alkaryl, aralkyl or heterocyclic, which can be substituted with groups which are substantially inert to any component of the reaction mixture under conditions selected for preparation of the amido-amine. Such substituent groups include hydroxy, halide (e.g., Cl, F, I, Br), $-\text{SH}$ and alkylthio. When one or more of R^5 through R^9 are alkyl, such alkyl groups can be straight or branched chain, and will generally contain from 1 to 20, more usually from 1 to 10, and preferably from 1 to 4, carbon atoms. Illustrative of such alkyl groups are methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, dodecyl, tridecyl, hexadecyl, octadecyl and the like. When one or more of R^5 through R^9 are aryl, the aryl group will generally contain from 6 to 10 carbon atoms (e.g., phenyl, naphthyl).

When one or more of R^5 through R^9 are alkaryl, the alkaryl group will generally contain from about 7 to 20 carbon atoms, and preferably from 7 to 12 carbon atoms. Illustrative of such alkaryl groups are tolyl, m-ethylphenyl, o-ethyltolyl, and m-hexyltolyl. When one or more of R^5 through R^9 are aralkyl, the aryl component generally consists of phenyl or (C_1 to C_6) alkyl-substituted phenol and the alkyl component generally contains from 1 to 12 carbon atoms, and preferably from 1 to 6 carbon atoms. Examples of such aralkyl groups are benzyl, o-ethylbenzyl, and 4-isobutylbenzyl. When one or more of R^5 and R^9 are cycloalkyl, the cycloalkyl group will generally contain from 3 to 12 carbon atoms, and preferably from 3 to 6 carbon atoms. Illustrative of such cyc-


loalkyl groups are cyclopropyl, cyclobutyl, cyclohexyl, cyclooctyl, and cyclododecyl. When one or more of R⁶ through R⁹ are heterocyclic, the heterocyclic group generally consists of a compound having at least one ring of 6 to 12 members in which one or more ring carbon atoms is replaced by oxygen or nitrogen. Examples of such heterocyclic groups are furyl, pyranyl, pyridyl, piperidyl, dioxanyl, tetrahydrofuryl, pyrazinyl and 1,4-oxazinyl.

The alpha, beta ethylenically unsaturated carboxylate compounds employed herein have the following formula :




wherein R⁵, R⁶, R⁷, and R⁸ are the same or different and are hydrogen or substituted or unsubstituted hydrocarbyl as defined above. Examples of such alpha, beta-ethylenically unsaturated carboxylate compounds of formula XI are acrylic acid, methacrylic acid, the methyl, ethyl, isopropyl, n-butyl, and isobutyl esters of acrylic and methacrylic acids, 2-butenic acid, 2-hexenoic acid, 2-decenoic acid, 3-methyl-2-heptenoic acid, 3-methyl-2-butenic acid, 3-phenyl-2-propenoic acid, 3-cyclohexyl-2-butenic acid, 2-methyl-2-butenic acid, 2-propyl-2-propenoic acid, 2-isopropyl-2-hexenoic acid, 2,3-dimethyl-2-butenic acid, 3-cyclohexyl-2-methyl-2-penten-2-ic acid, 2-propenoic acid, methyl 2-propenoate, methyl 2-methyl 2-propenoate, methyl 2-butenate, ethyl 2-hexenoate, isopropyl 2-decenoate, phenyl 2-pentenoate, tertiary butyl 2-propenoate, octadecyl 2-propenoate, dodecyl 2-decenoate, cyclopropyl 2,3-dimethyl-2-butenate, methyl 3-phenyl-2-propenoate, and the like.

The alpha, beta ethylenically unsaturated carboxylate thioester compounds employed herein have the following formula :




wherein R⁵, R⁶, R⁷, and R⁸ are the same or different and are hydrogen or substituted or unsubstituted hydrocarbyl as defined above. Examples of such alpha, beta-ethylenically unsaturated carboxylate thioesters of formula XII are methylmercapto 2-butenate, ethylmercapto 2-hexenoate, isopropylmercapto 2-decenoate, phenylmercapto 2-pentenoate, tertiary butylmercapto 2-propenoate, octadecylmercapto 2-propenoate, dodecylmercapto 2-decenoate, cyclopropylmercapto 2,3-dimethyl-2-butenate, methylmercapto 3-phenyl-2-propenoate, methylmercapto 2-propenoate, methylmercapto 2-methyl-2-propenoate, and the like.

The alpha, beta ethylenically unsaturated carboxamide compounds employed herein have the following formula :



wherein R⁵, R⁶, R⁷, R⁸ and R⁹ are the same or different and are hydrogen or substituted or unsubstituted hydrocarbyl as defined above. Examples of alpha, beta-ethylenically unsaturated carboxamides of formula XIII are 2-butenamide, 2-hexenamide, 2-decenamide, 3-methyl-2-heptenamide, 3-methyl-2-butenamide, 3-phenyl-2-propenamide, 3-cyclohexyl-2-butenamide, 2-methyl-2-butenamide, 2-propyl-2-propenamide, 2-isopropyl-2-hexenamide, 2,3-dimethyl-2-butenamide, 3-cyclohexyl-2-methyl-2-pentenamide, N-methyl 2-butenamide, N,N-diethyl 2-hexenamide, N-isopropyl 2-decenamide, N-phenyl 2-pentenamide, N-tertiary butyl 2-propenamide, N-octadecyl 2-propenamide, N,N-didodecyl 2-decenamide, N-cyclopropyl 2,3-dimethyl-2-butenamide, N-methyl 3-phenyl-2-propenamide, 2-propenamide, 2-methyl-2-propenamide, 2-ethyl-2-propenamide and the like.


The alpha, beta ethylenically unsaturated thiocarboxylate compounds employed herein have the following formula :



wherein R⁵, R⁶, R⁷, R⁸ and R⁹ are the same or different and are hydrogen or substituted or unsubstituted hydro-


rocarbonyl as defined above. Examples of alpha, beta-ethylenically unsaturated thiocarboxylate compounds of formula XIV are 2-butenthioic acid, 2-hexenthioic acid, 2-decenthioic acid, 3-methyl-2-heptenthioic acid, 3-methyl-2-butenthioic acid, 3-phenyl-2-propenthioic acid, 3-cyclohexyl-2-butenthioic acid, 2-methyl-2-butenthioic acid, 2-propyl-2-propenthioic acid, 2-isopropyl-2-hexenthioic acid, 2,3-dimethyl-2-butenthioic acid, 3-cyclohexyl-2-methyl-2-pententhioic acid, 2-propenthioic acid, methyl 2-propenthioate, methyl 2-methyl-2-propenthioate, methyl 2-butenthioate, ethyl 2-hexenthioate, isopropyl 2-decenthioate, phenyl 2-pententhioate, tertiary butyl 2-propenthioate, octadecyl 2-propenthioate, dodecyl 2-decenthioate, cyclopropyl 2,3-dimethyl-2-butenthioate, methyl 3-phenyl-2-propenthioate, and the like.

The alpha, beta ethylenically unsaturated dithioic acid and acid ester compounds employed herein have the following formula :




wherein R^5 , R^6 , R^7 , and R^8 are the same or different and are hydrogen or substituted or unsubstituted hydrocarbonyl as defined above. Examples of alpha, beta-ethylenically unsaturated dithioic acids and acid esters of formula XV are 2-butendithioic acid, 2-hexendithioic acid, 2-decendithioic acid, 3-methyl-2-heptendithioic acid, 3-methyl-2-butendithioic acid, 3-phenyl-2-propendithioic acid, 3-cyclohexyl-2-butendithioic acid, 2-methyl-2-butendithioic acid, 2-propyl-2-propendithioic acid, 2-isopropyl-2-hexendithioic acid, 2,3-dimethyl-2-butendithioic acid, 3-cyclohexyl-2-methyl-2-pentendithioic acid, 2-propendithioic acid, methyl 2-propendithioate, methyl 2-methyl-2-propendithioate, methyl 2-butendithioate, ethyl 2-hexendithioate, isopropyl 2-decendithioate, phenyl 2-pentendithioate, tertiary butyl 2-propendithioate, octadecyl 2-propendithioate, dodecyl 2-decendithioate, cyclopropyl 2,3-dimethyl-2-butendithioate, methyl 3-phenyl-2-propendithioate, and the like.

The alpha, beta ethylenically unsaturated thiocarboxamide compounds employed herein have the following formula :



wherein R^5 , R^6 , R^7 , R^8 and R^9 are the same or different and are hydrogen or substituted or unsubstituted hydrocarbonyl as defined above. Examples of alpha, beta-ethylenically unsaturated thiocarboxamides of formula XVI are 2-butenthioamide, 2-hexenthioamide, 2-decenthioamide, 3-methyl-2-heptenthioamide, 3-methyl-2-butenthioamide, 3-phenyl-2-propenthioamide, 3-cyclohexyl-2-butenthioamide, 2-methyl-2-butenthioamide, 2-propyl-2-propenthioamide, 2-isopropyl-2-hexenthioamide, 2,3-dimethyl-2-butenthioamide, 3-cyclohexyl-2-methyl-2-pententhioamide, N-methyl 2-butenthioamide, N,N-diethyl 2-hexenthioamide, N-isopropyl 2-decenthioamide, N-phenyl 2-pententhioamide, N-tertiary butyl 2-propenthioamide, N-octadecyl 2-propenthioamide, N-N-didodecyl 2-decenthioamide, N-cyclopropyl 2,3-dimethyl-2-butenthioamide, N-methyl 3-phenyl-2-propenthioamide, 2-propenthioamide, 2-methyl-2-propenthioamide, 2-ethyl-2-propenthioamide and the like.

Preferred compounds for reaction with the polyamines in accordance with this invention are lower alkyl esters of acrylic and (lower alkyl) substituted acrylic acid. Illustrative of such preferred compounds are compounds of the formula :




where R^7 is hydrogen or a C_1 to C_4 alkyl group, such as methyl, and R^8 is hydrogen or a C_1 to C_4 alkyl group, capable of being removed so as to form an amido group, for example, methyl, ethyl, propyl, isopropyl, butyl, sec-butyl, tert-butyl, aryl, hexyl, etc. In the preferred embodiments these compounds are acrylic and methacrylic esters such as methyl or ethyl acrylate, methyl or ethyl methacrylate. When the selected alpha, beta-unsaturated compound comprises a compound of formula X wherein X' is oxygen, the resulting reaction product with the polyamine contains at least one amido linkage ($-C(O)N<$) and such materials are herein termed "amidoamines." Similarly, when the selected alpha, beta unsaturated compound of formula X comprises a compound wherein X' is sulfur, the resulting reaction product with the polyamine contains thioamide linkage ($-C(S)N<$) and these materials are herein termed "thioamidoamines." For convenience, the following discussion is directed

to the preparation and use of amido-amines, although it will be understood that such discussion is also applicable to thioamido-amines.


The type of amido-amine formed varies with reaction conditions. For example, a more linear amido-amine is formed where substantially equimolar amounts of the unsaturated carboxylate and polyamine are reacted. The presence of excesses of the ethylenically unsaturated reactant of formula X tends to yield an amido-amine which is more cross-linked than that obtained where substantially equimolar amounts of reactants are employed. Where for economic or other reasons a cross-linked amido-amine using excess amine is desired, generally a molar excess of the ethylenically unsaturated reactant of about at least 10%, such as 10-300%, or greater, for example, 25-200%, is employed. For more efficient cross-linking an excess of carboxylated material should preferably be used since a cleaner reaction ensues. For example, a molar excess of about 10-100% or greater such as 10-50%, but preferably an excess of 30-50%, of the carboxylated material. Larger excesses can be employed if desired.

In summary, without considering other factors, equimolar amounts of reactants tend to produce a more linear amido-amine whereas excess of the formula XII reactant tends to yield a more cross-linked amido-amine. It should be noted that the higher the polyamine (i.e., in greater the number of amino groups on the molecule) the greater the statistical probability of cross-linking since, for example, a tetraalkylenepentamine, such as tetraethylene pentamine



has more labile hydrogens than ethylene diamine.

These amido-amine adducts so formed are characterized by both amido and amino groups. In their simplest embodiments they may be represented by units of the following idealized formula (XVIII) :



wherein the R^{10} 's, which may be the same or different, are hydrogen or a substituted group, such as a hydrocarbon group, for example, alkyl, alkenyl, alkynyl, aryl, etc., and A is a moiety of the polyamine which, for example, may be aryl, cycloalkyl, alkyl, etc., and n_4 is an integer such as 1-10 or greater.

The above simplified formula represents a linear amido-amine polymer. However, cross-linked polymers may also be formed by employing certain conditions since the polymer has labile hydrogens which can further react with either the unsaturated moiety by adding across the double bond or by amidifying with a carboxylate group.

Preferably, however, the amido-amines employed in this invention are not cross-linked to any substantial degree, and more preferably are substantially linear.

Preferably, the polyamine reactant contains at least one primary amine (and more preferably from 2 to 4 primary amines) group per molecule, and the polyamine and the unsaturated reactant of formula X are contacted in an amount of from about 1 to 10, more preferably from about 2 to 6, and most preferably from about 3 to 5, equivalents of primary amine in the polyamine reactant per mole of the unsaturated reactant of formula X.


The reaction between the selected polyamine and acrylate-type compound is carried out at any suitable temperature. Temperatures up to the decomposition points of reactants and products can be employed. In practice, one generally carries out the reaction by heating the reactants below 100°C, such as 80-90°C, for a suitable period of time, such as a few hours. Where an acrylic-type ester is employed, the progress of the reaction can be judged by the removal of the alcohol in forming the amide. During the early part of the reaction alcohol is removed quite readily below 100°C in the case of low boiling alcohols such as methanol or ethanol. As the reaction slows, the temperature is raised to push the polymerization to completion and the temperature may be raised to 150°C toward the end of the reaction. Removal of alcohol is a convenient method of judging the progress and completion of the reaction which is generally continued until no more alcohol is evolved. Based on removal of alcohol, the yields are generally stoichiometric. In more difficult reactions, yield of at least 95% are generally obtained.

Similarly, it will be understood that the reaction of an ethylenically unsaturated carboxylate thio ester of for-

mula XII liberates the corresponding HSR⁸ compound (e.g., H₂S when R⁸ is hydrogen) as a by-product, and the reaction of an ethylenically unsaturated carboxyamide of formula XIII liberates the corresponding HNR⁸(R⁹) compound (e.g., ammonia when R⁸ and R⁹ are each hydrogen) as by-product.

The reaction time to form an amido-amine material can vary widely depending on a wide variety of factors. For example, there is a relationship between time and temperature. In general, lower temperature demands longer times. Usually, reaction times of from about 2 to 30 hours, such as 5 to 25 hours, and preferably 3 to 10 hours will be employed. Although one can employ a solvent, the reaction can be run without the use of any solvent. In fact, where a high degree of cross-linking is desired, it is preferably to avoid the use of a solvent and most particularly to avoid a polar solvent such as water. However, taking into consideration the effect of solvent on the reaction, where desired, any suitable solvent can be employed, whether organic or inorganic, polar or non-polar.

As an example of the amido-amine adducts, the reaction of tetraethylene pentaamine (TEPA) with methyl methacrylate can be illustrated as follows :




CONDENSATION REACTION

The Mannich Base condensate dispersants of this invention are prepared by condensing at least one of the above described alkylated hydroxyaromatic compounds with an amine in the presence of an aldehyde. The reactants are contacted for a time and under conditions sufficient to form the desired dispersant product.


The process employed in the condensation reaction can be any of those disclosed in U.S. Patents 3,634,515 ; 3,649,229 ; 3,442,808 ; 3,798,165 ; 3,798,247 ; and 3,539,633, the disclosures of which are hereby incorporated by reference in their entirety.

The amount of the reactants employed is not critical and can vary over a wide range. It is, however, preferred to react the alkylated hydroxy aromatic compound, aldehyde reactant and amine compound in the respective molar ratios of about 1 : 1-4 : 0.1-10. An excess of aldehyde reactant may be used. The reactions are exothermic, but it is desirable to heat the reaction to a temperature of above about 150°C, preferably in the range of from about 150 - 200°C. This additional heating drives the reaction to completion and removes water from the resultant condensation reaction product.

The condensation reaction can be illustrated by the following reactions employing an alkylene polyamine and formaldehyde :



wherein "z" is an integer of from 1 to 10, "a" is an integer of 1 or 2 and "EP" is an ethylene-propylene copolymer as described above, and



wherein "z", and "EP" are as defined above.

20 A preferred group of Mannich Base ashless dispersants are those formed by condensing ethylene-propylene copolymer-substituted phenol with formaldehyde and polyethylene amines, e.g., tetraethylene pentamine, pentaethylene hexamine, polyoxyethylene and polyoxypropylene amines, e.g., polyoxypropylene diamine, and combinations thereof. One particularly preferred dispersant comprises a condensation of (A) ethylene-propylene copolymer-substituted phenol, (B) formaldehyde, (C) a polyoxyalkylene polyamine, e.g., polyoxypropylene diamine, and (D) a polyalkylene polyamine, e.g. polyethylene diamine and tetraethylene pentamine, using

25 about 2 to about 8 moles each of (B) and about 1 to about 4 moles of (C) or (D) per mole of (A). The reaction product mixture comprising the desired ethylene-alpha-olefin substituted Mannich Base condensation product formed by the process of this invention will generally be present in the condensation reaction product mixture in a concentration of at least about 60 wt.% (e.g., from 65 to 95 wt.%), more preferably at least about 70 wt.%, from 75 to 90 wt.%, and will be generally characterized by a VR value ("viscosity ratio" value)

30 of not greater than about 4.1, usually not greater than about 4.0, preferably from about 2.5 to 4.0, and most preferably from about 3.0 to 3.9. As used herein, the term "VR value" is intended to mean quotient determined by the expression (IV) :

$$\text{VR} = \frac{\text{VISb}}{\text{VISa}}$$

35 wherein VISa is the kinematic viscosity (KV) of the condensation reaction product mixture at 100°C in units of centistokes (as determined by ASTM Method No. D445) and VISb is the cold cranking simulator (CCS) viscosity of the condensation reaction product mixture at -20°C in units of poise (as determined by ASTM Method No. D2602), wherein the measurements are made upon a 2 wt% solution of the condensation reaction product mixture in an oil (herein termed the "reference oil") comprising S150N (solvent 150 neutral) mineral lubricating oil (Exxon Company U.S.A.), wherein the such reference oil is characterized by an ASTM D445 kinematic viscosity

40 of 5.2 cSt (100°C) and an ASTM D2602 CCS viscosity of 19.2 poise (± 0.4 poise) (at -20°C). The "VR_r" value of the reference oil will then be about 3.7 ± 0.1 .

Another aspect of this invention involves the post treatment of the nitrogen containing dispersant materials. The process for post-treating said nitrogen containing dispersant materials is analogous to the post-treating processes used with respect to derivatives of conventional ethylene copolymers of the prior art. Accordingly,

45 the same reaction conditions, ratio of reactants and the like can be used.

The nitrogen-containing dispersant materials of the instant invention as described above are post-treated by contacting said nitrogen-containing dispersant materials with one or more post-treating reagents selected from the group consisting of boron oxide, boron oxide hydrate, boron halides, boron acids, esters of boron acids, carbon disulfide, sulfur, sulfur chlorides, alkenyl cyanides, aldehydes, ketones, urea, thio-urea, guanidine, dicyanodiamide, hydrocarbyl phosphates, hydrocarbyl phosphites, hydrocarbyl thiophosphates, hydrocarbyl thiophosphites, phosphorus sulfides, phosphorus oxides, phosphoric acid, hydrocarbyl thiocyanates, hydrocarbyl isocyanates, hydrocarbyl isothiocyanates, epoxides, episulfides, formaldehyde or formaldehyde-producing compounds plus phenols, and sulfur plus phenols, and C₁ to C₃₀ hydrocarbyl substituted succinic acids and anhydrides (e.g., succinic anhydride, dodecyl succinic anhydride and the like), fumaric acid, itaconic acid,

50 maleic acid, maleic anhydride, chloromaleic acid, chloromaleic anhydride, acrylic acid, methacrylic acid, crotonic acid, cinnamic acid, and lower alkyl (e.g., C₁ to C₄ alkyl) acid esters of the foregoing, e.g., methyl maleate, ethyl fumarate, methyl fumarate, and the like.

55

For example, the nitrogen containing dispersants can be treated with a boron compound selected from the class consisting of boron oxide, boron halides, boron acids and esters of boron acids in an amount to provide

from about 0.1 atomic proportion of boron for each mole of said nitrogen composition to about 20 atomic proportions of boron for each atomic proportion of nitrogen of said nitrogen composition. Usefully the borated dispersants of the invention contain from about 0.05 to 2.0 wt. %, e.g. 0.05 to 0.7 wt. % boron based on the total weight of said borated nitrogen-containing dispersant compound. The boron, which appears to be in the product as dehydrated boric acid polymers (primarily $(\text{HBO}_2)_3$), is believed to attach to the dispersant as amine salts, e.g., the metaborate salt of said amine dispersants.

Treating is readily carried out by adding from about 0.05 to 4, e.g. 1 to 3 wt. % (based on the weight of said nitrogen compound) of said boron compound, preferably boric acid which is most usually added as a slurry to said nitrogen compound and heating with stirring at from about 135°C. to 190, e.g. 140-170°C., for from 1 to 5 hours followed by nitrogen stripping at said temperature ranges.


Since post-treating processes involving the use of these post-treating reagents is known insofar as application to high molecular weight nitrogen containing dispersants of the prior art, further descriptions of these processes herein is unnecessary. In order to apply the prior art processes to the compositions of this invention, all that is necessary is that reaction conditions, ratio of reactants, and the like as described in the prior art, be applied to the novel compositions of this invention. The following U.S. patents are expressly incorporated herein by reference for their disclosure of post-treating processes and post-treating reagents applicable to the compositions of this invention : U.S. Pat. Nos. 3,087,936 ; 3,200,107 ; 3,254,025 ; 3,256,185 ; 3,278,550 ; 3,281,428 ; 3,282,955 ; 3,284,410 ; 3,338,832 ; 3,344,069 ; 3,366,569 ; 3,373,111 ; 3,367,943 ; 3,390,086 ; 3,403,102 ; 3,428,561 ; 3,470,098 ; 3,502,677 ; 3,513,093 ; 3,533,945 ; 3,541,012 ; 3,558,743 ; 3,639,242 ; 3,708,522 ; 3,859,318 ; 3,865,813 ; 3,470,098 ; 3,369,021 ; 3,184,411 ; 3,185,645 ; 3,245,908 ; 3,245,909 ; 3,245,910 ; 3,573,205 ; 3,692,681 ; 3,749,695 ; 3,865,740 ; 3,954,639 ; 3,458,530 ; 3,390,086 ; 3,367,943 ; 3,185,704 ; 3,551,466 ; 3,415,750 ; 3,312,619 ; 3,280,034 ; 3,718,663 ; 3,652,616 ; 4,338,205 ; 4,428,849 ; 4,686,054 ; 4,839,070 ; 4,839,071 ; 4,839,072 ; 4,839,073 ; U.K. Pat. No. 1,085,903 ; U.K. Pat. No. 1,162,436.

The nitrogen containing dispersant materials of this invention can also be treated with polymerizable lactones (such as epsilon-caprolactone) to form dispersant adducts having the moiety $-\text{C}(\text{O})(\text{CH}_2)_z\text{O}-$, wherein z is a number of from 4 to 8 (e.g., 5 to 7) and m has an average value of from about 0 to 100 (e.g., 0.2 to 20). The dispersants of this invention can be post-treated with a C_5 to C_9 lactone, e.g., epsilon-caprolactone, by heating a mixture of the dispersant material and lactone in a reaction vessel in the absence of a solvent at a temperature of about 50°C to about 200°C, more preferably from about 75°C to about 180°C, and most preferably from about 90°C to about 160°C, for a sufficient period of time to effect reaction. Optionally, a solvent for the lactone, dispersant material and/or the resulting adduct may be employed to control viscosity and/or the reaction rates.

In one preferred embodiment, the C_5 to C_9 lactone, e.g., epsilon-caprolactone, is reacted with a dispersant material in a 1 : 1 mole ratio of lactone to dispersant material. In practice, the ration of lactone to dispersant material may vary considerably as a means of controlling the length of the sequence of the lactone units in the adduct. For example, the mole ratio of the lactone to the dispersant material may vary from about 10 : 1 to about 0.1 : 1, more preferably from about 5 : 1 to about 0.2 : 1, and most preferably from about 2 : 1 to about 0.4 : 1. It is preferable to maintain the average degree of polymerization of the lactone monomer below about 100, with a degree of polymerization on the order of from about 0.2 to about 50 being preferred, and from about 0.2 to about 20 being more preferred. For optimum dispersant performance, sequences of from about 1 to about 5 lactone units in a row are preferred.

Catalysts useful in the promotion of the lactone-dispersant material reactions are selected from the group consisting of stannous octanoate, stannous hexanoate, tetrabutyl titanate, a variety of organic based acid catalysts and amine catalysts, as described on page 266, and forward, in a book chapter authored by R.D. Lundberg and E. F. Cox, entitled "Kinetics and Mechanisms of Polymerization : Ring Opening Polymerization", edited by Frisch and Reegen, published by Marcel Dekker in 1969, wherein stannous octanoate is an especially preferred catalyst. The catalyst is added to the reaction mixture at a concentration level of about 50 to about 10,000 parts per weight of catalyst per one million parts of the total reaction mixture.

Exemplary of adducts formed by reaction of dispersant materials of this invention and epsilon-caprolactone are those adducts illustrated by the following equation :



wherein m and EP are as defined above. The reactions of such lactones with dispersant materials containing nitrogen or ester groups is more completely described in U.S. Patents 4,486,326 ; 4,820,432 ; 4,828,742 ; 4,851,524 ; 4,866,135 ; 4,866,139 ; 4,866,140 ; 4,866,141 ; 4,866,142 ; and 4,866,187, the disclosure of each of which is hereby incorporated by reference in its entirety.

Further aspects of the present invention reside in the formation of metal complexes of the novel dispersant additives prepared in accordance with this invention. Suitable metal complexes may be formed in accordance with known techniques of employing a reactive metal ion species during or after the formation of the present dispersant materials. Complex forming metal reactants include the metal nitrates, thiocyanates, halides, carboxylates, phosphates, thio-phosphates, sulfates, and borates of transition metals such as iron, cobalt, nickel, copper, chromium, manganese, molybdenum, tungsten, ruthenium, palladium, platinum, cadmium, lead, silver, mercury, antimony and the like. Prior art disclosures of these complexing reactions may be also found in U.S. Patents 3,306,908 and Re. 26,433, the disclosures of which are hereby incorporated by reference in their entirety.

The processes of these incorporated patents, as applied to the compositions of this invention, and the post-treated compositions thus produced constitute a further aspect of this invention.

The dispersants of the present invention can be incorporated into a lubricating oil in any convenient way. Thus, these mixtures can be added directly to the oil by dispersing or dissolving the same in the oil at the desired level of concentrations of the dispersant and detergent, respectively. Such blending into the additional lube oil can occur at room temperature or elevated temperatures. Alternatively, the dispersants can be blended with a suitable oil-soluble solvent and base oil to form a concentrate, and then blending the concentrate with a lubricating oil basestock to obtain the final formulation. Such dispersant concentrates will typically contain (on an active ingredient (A.I.) basis) from about 20 to about 60 wt.%, and preferably from about 40 to about 50 wt.%, dispersant additive, and typically from about 40 to 80 wt.%, preferably from about 40 to 60 wt.%, base oil, based on the concentrate weight. The lubricating oil basestock for the dispersant typically is adapted to perform a selected function by the incorporation of additional additives therein to form lubricating oil compositions (i.e., formulations).

LUBRICATING COMPOSITIONS

The additive mixtures of the present invention possess very good dispersant properties as measured herein in a wide variety of environments. Accordingly, the additive mixtures are used by incorporation and dissolution into an oleaginous material such as fuels and lubricating oils. When the additive mixtures of this invention are used in normally liquid petroleum fuels such as middle distillates boiling from about 65° to 430°C, including

5 kerosene, diesel fuels, home heating fuel oil, jet fuels, etc., a concentration of the additives in the fuel in the range of typically from about 0.001 to about 0.5, and preferably 0.005 to about 0.15 weight percent, based on the total weight of the composition, will usually be employed.

The additive mixtures of the present invention find their primary utility in lubricating oil compositions which employ a base oil in which the additives are dissolved or dispersed. Such base oils may be natural or synthetic. Base oils suitable for use in preparing the lubricating oil compositions of the present invention include those conventionally employed as crankcase lubricating oils for spark-ignited and compression-ignited internal combustion engines, such as automobile and truck engines, marine and railroad diesel engines, and the like. Advantageous results are also achieved by employing the additive mixtures of the present invention in base oils conventionally employed in and/or adapted for use as power transmitting fluids, universal tractor fluids and hydraulic fluids, heavy duty hydraulic fluids, power steering fluids and the like. Gear lubricants, industrial oils, pump oils and other lubricating oil compositions can also benefit from the incorporation therein of the additive mixtures of the present invention.

These lubricating oil formulations conventionally contain several different types of additives that will supply the characteristics that are required in the formulations. Among these types of additives are included viscosity index improvers, antioxidants, corrosion inhibitors, detergents, dispersants, pour point depressants, antiwear agents, friction modifiers, etc.

20 In the preparation of lubricating oil formulations it is common practice to introduce the additives in the form of 10 to 80 wt. %, e.g., 20 to 80 wt. % active ingredient concentrates in hydrocarbon oil, e.g. mineral lubricating oil, or other suitable solvent. Usually these concentrates may be diluted with 3 to 100, e.g., 5 to 40 parts by weight of lubricating oil, per part by weight of the additive package, in forming finished lubricants, e.g. crankcase motor oils. The purpose of concentrates, of course, is to make the handling of the various materials less difficult and awkward as well as to facilitate solution or dispersion in the final blend. Thus, a dispersant would be usually employed in the form of a 40 to 50 wt. % concentrate, for example, in a lubricating oil fraction.

The ashless dispersants of the present invention will be generally used in admixture with a lube oil base-stock, comprising an oil of lubricating viscosity, including natural and synthetic lubricating oils and mixtures thereof.

30 Natural oils include animal oils and vegetable oils (e.g., castor, lard oil) liquid petroleum oils and hydrorefined, solvent-treated or acid-treated mineral lubricating oils of the paraffinic, naphthenic and mixed paraffinic-naphthenic types. Oils of lubricating viscosity derived from coal or shale are also useful base oils.

Alkylene oxide polymers and interpolymers and derivatives thereof where the terminal hydroxyl groups have been modified by esterification, etherification, etc., constitute another class of known synthetic lubricating oils. These are exemplified by polyoxyalkylene polymers prepared by polymerization of ethylene oxide or propylene oxide, the alkyl and aryl ethers of these polyoxyalkylene polymers (e.g., methyl-poly isopropylene glycol ether having an average molecular weight of 1000, diphenyl ether of poly-ethylene glycol having a molecular weight of 500-1000, diethyl ether of polypropylene glycol having a molecular weight of 1000-1500); and mono- and polycarboxylic esters thereof, for example, the acetic acid esters, mixed C₃-C₈ fatty acid esters and C₁₃ Oxo acid diester of tetraethylene glycol.

Another suitable class of synthetic lubricating oils comprises the esters of dicarboxylic acids (e.g., phthalic acid, succinic acid, alkyl succinic acids and alkenyl succinic acids, maleic acid, azelaic acid, suberic acid, sebacic acid, fumaric acid, adipic acid, linoleic acid dimer, malonic acid, alkylmalonic acids, alkenyl malonic acids) with a variety of alcohols (e.g., butyl alcohol, hexyl alcohol, dodecyl alcohol, 2-ethylhexyl alcohol, ethylene glycol, diethylene glycol monoether, propylene glycol). Specific examples of these esters include dibutyl adipate, di (2-ethylhexyl)sebacate, di-n-hexyl fumarate, dioctyl sebacate, diisooctyl azelate, diisodecyl azelate, dioctyl phthalate, didecyl phthalate, dieicosyl sebacate, the 2-ethylhexyl diester of linoleic acid dimer, and the complex ester formed by reacting one mole of sebacic acid with two moles of tetraethylene glycol and two moles of 2-ethylhexanoic acid.

50 Esters useful as synthetic oils also include those made from C₆ to C₁₂ monocarboxylic acids and polyols and polyol ethers such as neopentyl glycol, trimethylolpropane, pentaerythritol, dipentaerythritol and tripentaerythritol.

Silicon-based oils such as the polyalkyl-, polyaryl-, polyalkoxy-, or polyaryloxysiloxane oils and silicate oils comprise another useful class of synthetic lubricants; they include tetraethyl silicate, tetraisopropyl silicate, tetra-(2-ethylhexyl)silicate, tetra-(4-methyl-2-ethylhexyl)silicate, tetra-(p-tertbutylphenyl)silicate, hexa-(4-methyl-2-pentoxy)disiloxane, poly(methyl)siloxanes and poly(methylphenyl)siloxanes. Other synthetic lubricating oils include liquid esters of phosphorus-containing acids (e.g., tricresyl phosphat, trioctyl phosphat, diethyl ster of decylphosphonic acid) and polymeric tetrahydrofurans.

Unrefined, refined and rerefined oils can be used in the lubricants of the present invention. Unrefined oils are those obtained directly from a natural or synthetic source without further purification treatment. For example,

a shale oil obtained directly from retorting operations, a petroleum oil obtained directly from distillation or ester oil obtained directly from an esterification process and used without further treatment would be an unrefined oil. Refined oils are similar to the unrefined oils except they have been further treated in one or more purification steps to improve one or more properties. Many such purification techniques, such as distillation, solvent extraction, acid or base extraction, filtration and percolation are known to those skilled in the art. Refined oils are obtained by processes similar to those used to obtain refined oils applied to refined oils which have been already used in service. Such re-refined oils are also known as reclaimed or reprocessed oils and often are additionally processed by techniques for removal of spent additives and oil breakdown products.

Metal containing rust inhibitors and/or detergents are frequently used with ashless dispersants. Such detergents and rust inhibitors include the metal salts of sulphonic acids, alkyl phenols, sulphurized alkyl phenols, alkyl salicylates, naphthenates, and other oil soluble mono- and di-carboxylic acids. Highly basic, that is over-based metal salts which are frequently used as detergents appear particularly prone to interaction with the ashless dispersant. Usually these metal containing rust inhibitors and detergents are used in lubricating oil in amounts of about 0.01 to 10, e.g. 0.1 to 5 wt. %, based on the weight of the total lubricating composition. Marine diesel lubricating oils typically employ such metal-containing rust inhibitors and detergents in amounts of up to about 20 wt. %.

Highly basic alkaline earth metal sulfonates are frequently used as detergents. They are usually produced by heating a mixture comprising an oil-soluble sulfonate or alkaryl sulfonic acid, with an excess of alkaline earth metal compound above that required for complete neutralization of any sulfonic acid present and thereafter forming a dispersed carbonate complex by reacting the excess metal with carbon dioxide to provide the desired overbasing. The sulfonic acids are typically obtained by the sulfonation of alkyl substituted aromatic hydrocarbons such as those obtained from the fractionation of petroleum by distillation and/or extraction or by the alkylation of aromatic hydrocarbons as for example those obtained by alkylating benzene, toluene, xylene, naphthalene, diphenyl and the halogen derivatives such as chlorobenzene, chlorotoluene and chloronaphthalene. The alkylation may be carried out in the presence of a catalyst with alkylating agents having from about 3 to more than 30 carbon atoms. For example haloparaffins, olefins obtained by dehydrogenation of paraffins, polyolefins produced from ethylene, propylene, etc. are all suitable. The alkaryl sulfonates usually contain from about 9 to about 70 or more carbon atoms, preferably from about 16 to about 50 carbon atoms per alkyl substituted aromatic moiety.

The alkaline earth metal compounds which may be used in neutralizing these alkaryl sulfonic acids to provide the sulfonates includes the oxides and hydroxides, alkoxides, carbonates, carboxylate, sulfide, hydrosulfide, nitrate, borates and ethers of magnesium, calcium, and barium. Examples are calcium oxide, calcium hydroxide, magnesium acetate and magnesium borate. As noted, the alkaline earth metal compound is used in excess of that required to complete neutralization of the alkaryl sulfonic acids. Generally, the amount ranges from about 100 to 220%, although it is preferred to use at least 125%, of the stoichiometric amount of metal required for complete neutralization.

Various other preparations of basic alkaline earth metal alkaryl sulfonates are known, such as U.S. Patents 3,150,088 and 3,150,089 wherein overbasing is accomplished by hydrolysis of an alkoxide-carbonate complex with the alkaryl sulfonate in a hydrocarbon solvent-diluent oil.

A preferred alkaline earth sulfonate additive is magnesium alkyl aromatic sulfonate having a total base number ranging from about 300 to about 400 with the magnesium sulfonate content ranging from about 25 to about 32 wt. %, based upon the total weight of the additive system dispersed in mineral lubricating oil.


Neutral metal sulfonates are frequently used as rust inhibitors. Polyvalent metal alkyl salicylate and naphthenate materials are known additives for lubricating oil compositions to improve their high temperature performance and to counteract deposition of carbonaceous matter on pistons (U.S. Patent 2,744,069). An increase in reserve basicity of the polyvalent metal alkyl salicylates and naphthenates can be realized by utilizing alkaline earth metal, e.g. calcium, salts of mixtures of C_8 - C_{26} alkyl salicylates and phenates (see U.S. Patent 2,744,069) or polyvalent metal salts of alkyl salicylic acids, said acids obtained from the alkylation of phenols followed by phenation, carboxylation and hydrolysis (U.S. Patent 3,704,315) which could then be converted into highly basic salts by techniques generally known and used for such conversion. The reserve basicity of these metal-containing rust inhibitors is usefully at TBN levels of between about 60 and 150. Included with the useful polyvalent metal salicylate and naphthenate materials are the methylene and sulfur bridged materials which are readily derived from alkyl substituted salicylic or naphthenic acids or mixtures of either or both with alkyl substituted phenols. Basic sulfurized salicylates and a method for their preparation is shown in U.S. Patent 3,595,791. Such materials include alkaline earth metal, particularly magnesium, calcium, strontium and barium salts of aromatic acids having the general formula:



where Ar is an aryl radical of 1 to 6 rings, R_1 is an alkyl group having from about 8 to 50 carbon atoms, preferably


12 to 30 carbon atoms (optimally about 12), X is a sulfur (-S-) or methylene (-CH₂-) bridge, y is a number from 0 to 4 and n is a number from 0 to 4.

Preparation of the overbased methylene bridged salicylate-phenate salt is readily carried out by conventional techniques such as by alkylation of a phenol followed by phenation, carboxylation, hydrolysis, methylene bridging using a coupling agent such as an alkylene dihalide followed by salt formation concurrent with carbonation. An overbased calcium salt of a methylene bridged phenol-salicylic acid of the general formula (XIV) :



with a TBN of 60 to 150 is highly useful in this invention.

The sulfurized metal phenates can be considered the "metal salt of a phenol sulfide" which thus refers to a metal salt whether neutral or basic, of a compound typified by the general formula (XV) :



where $x = 1$ or 2 , $n = 0, 1$ or 2 ; or a polymeric form of such a compound, where R is an alkyl radical, n and x are each integers from 1 to 4, and the average number of carbon atoms in all of the R groups is at least about 9 in order to ensure adequate solubility in oil. The individual R groups may each contain from 5 to 40, preferably 8 to 20, carbon atoms. The metal salt is prepared by reacting an alkyl phenol sulfide with a sufficient quantity of metal containing material to impart the desired alkalinity to the sulfurized metal phenate.

Regardless of the manner in which they are prepared, the sulfurized alkyl phenols which are useful generally contain from about 2 to about 14% by weight, preferably about 4 to about 12 wt. % sulfur based on the weight of sulfurized alkyl phenol.

The sulfurized alkyl phenol may be converted by reaction with a metal containing material including oxides, hydroxides and complexes in an amount sufficient to neutralize said phenol and, if desired, to overbase the product to a desired alkalinity by procedures well known in the art. Preferred is a process of neutralization utilizing a solution of metal in a glycol ether.

The neutral or normal sulfurized metal phenates are those in which the ratio of metal to phenol nucleus is about 1:2. The "overbased" or "basic" sulfurized metal phenates are sulfurized metal phenates wherein the ratio of metal to phenol is greater than that of stoichiometric, e.g. basic sulfurized metal dodecyl phenate has a metal content up to and greater than 100% in excess of the metal present in the corresponding normal sulfurized metal phenates wherein the excess metal is produced in oil-soluble or dispersible form (as by reaction with CO₂).

Magnesium and calcium containing additives although beneficial in other respects can increase the tendency of the lubricating oil to oxidize. This is especially true of the highly basic sulphonates.

According to a preferred embodiment the invention therefore provides a crankcase lubricating composition also containing from 2 to 8000 parts per million of calcium or magnesium.

The magnesium and/or calcium is generally present as basic or neutral detergents such as the sulphonates and phenates, our preferred additives are the neutral or basic magnesium or calcium sulphonates. Preferably the oils contain from 500 to 5000 parts per million of calcium or magnesium. Basic magnesium and calcium sulphonates are preferred.

As indicated earlier, a particular advantage of the novel dispersants of the present invention is use with V.I. improvers to form multi-grade automobile engine lubricating oils. Viscosity modifiers impart high and low temperature operability to the lubricating oil and permit it to remain relatively viscous at elevated temperatures

and also exhibit acceptable viscosity or fluidity at low temperatures. Viscosity modifiers are generally high molecular weight hydrocarbon polymers including polyesters. The viscosity modifiers may also be derivatized to include other properties or functions, such as the addition of dispersancy properties. These oil soluble viscosity modifying polymers will generally have number average molecular weights of from 10^3 to 10^6 , preferably 10^4 to 10^5 , e.g., 20,000 to 250,000, as determined by gel permeation chromatography or osmometry.

Examples of suitable hydrocarbon polymers include homopolymers and copolymers of two or more monomers of C_2 to C_{30} , e.g. C_2 to C_8 olefins, including both alpha olefins and internal olefins, which may be straight or branched, aliphatic, aromatic, alkyl-aromatic, cycloaliphatic, etc. Frequently they will be of ethylene with C_3 to C_{30} olefins, particularly preferred being the copolymers of ethylene and propylene. Other polymers can be used such as polyisobutylenes, homopolymers and copolymers of C_6 and higher alpha olefins, atactic polypropylene, hydrogenated polymers and copolymers and terpolymers of styrene, e.g. with isoprene and/or butadiene and hydrogenated derivatives thereof. The polymer may be degraded in molecular weight, for example by mastication, extrusion, oxidation or thermal degradation, and it may be oxidized and contain oxygen. Also included are derivatized polymers such as post-grafted interpolymers of ethylene-propylene with an active monomer such as maleic anhydride which may be further reacted with an alcohol, or amine, e.g. an alkylene polyamine or hydroxy amine, e.g. see U.S. Patent Nos. 4,089,794 ; 4,160,739 ; 4,137,185 ; or copolymers of ethylene and propylene reacted or grafted with nitrogen compounds such as shown in U.S. Patent Nos. 4,068,056 ; 4,068,058 ; 4,146,489 and 4,149,984.

The preferred hydrocarbon polymers are ethylene copolymers containing from 15 to 90 wt.% ethylene, preferably 30 to 80 wt.% of ethylene and 10 to 85 wt.%, preferably 20 to 70 wt.% of one or more C_3 to C_{28} , preferably C_3 to C_{18} , more preferably C_3 to C_8 , alpha-olefins. While not essential, such copolymers preferably have a degree of crystallinity of less than 25 wt.%, as determined by X-ray and differential scanning calorimetry. Copolymers of ethylene and propylene are most preferred. Other alpha-olefins suitable in place of propylene to form the copolymer, or to be used in combination with ethylene and propylene, to form a terpolymer, tetrapolymer, etc., include 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, etc. ; also branched chain alpha-olefins, such as 4-methyl-1-pentene, 4-methyl-1-hexene, 5-methylpentene-1, 4,4-dimethyl-1-pentene, and 6-methylheptene-1, etc., and mixtures thereof.

Terpolymers, tetrapolymers, etc., of ethylene, said C_{3-28} alpha-olefin, and a non-conjugated diolefin or mixtures of such diolefins may also be used. The amount of the non-conjugated diolefin generally ranges from about 0.5 to 20 mole percent, preferably from about 1 to about 7 mole percent, based on the total amount of ethylene and alpha-olefin present.

The polyester V.I. improvers are generally polymers of esters of ethylenically unsaturated C_3 to C_8 mono- and dicarboxylic acids such as methacrylic and acrylic acids, maleic acid, maleic anhydride, fumaric acid, etc.

Examples of unsaturated esters that may be used include those of aliphatic saturated mono alcohols of at least 1 carbon atom and preferably of from 12 to 20 carbon atoms, such as decyl acrylate, lauryl acrylate, stearyl acrylate, eicosanyl acrylate, docosanyl acrylate, decyl methacrylate, diamyl fumarate, lauryl methacrylate, cetyl methacrylate, stearyl methacrylate, and the like and mixtures thereof.

Other esters include the vinyl alcohol esters of C_2 to C_{22} fatty or mono carboxylic acids, preferably saturated such as vinyl acetate, vinyl laurate, vinyl palmitate, vinyl stearate, vinyl oleate, and the like and mixtures thereof. Copolymers of vinyl alcohol esters with unsaturated acid esters such as the copolymer of vinyl acetate with dialkyl fumarates, can also be used.

The esters may be copolymerized with still other unsaturated monomers such as olefins, e.g. 0.2 to 5 moles of C_2 - C_{20} aliphatic or aromatic olefin per mole of unsaturated ester, or per mole of unsaturated acid or anhydride followed by esterification. For example, copolymers of styrene with maleic anhydride esterified with alcohols and amines are known, e.g., see U.S. Patent 3,702,300.

Such ester polymers may be grafted with, or the ester copolymerized with, polymerizable unsaturated nitrogen-containing monomers to impart dispersancy to the V.I. improvers. Examples of suitable unsaturated nitrogen-containing monomers include those containing 4 to 20 carbon atoms such as amino substituted olefins as p-(beta-diethylaminoethyl)styrene ; basic nitrogen-containing heterocycles carrying a polymerizable ethylenically unsaturated substituent, e.g. the vinyl pyridines and the vinyl alkyl pyridines such as 2-vinyl-5-ethyl pyridine, 2-methyl-5-vinyl pyridine, 2-vinyl-pyridine, 4-vinyl-pyridine, 3-vinyl-pyridine, 3-methyl-5-vinyl-pyridine, 4-methyl-2-vinyl-pyridine, 4-ethyl-2-vinyl-pyridine and 2-butyl-1-5-vinyl-pyridine and the like.

N-vinyl lactams are also suitable, e.g. N-vinyl pyrrolidones or N-vinyl piperidones.


The vinyl pyrrolidones are preferred and are exemplified by N-vinyl pyrrolidone, N-(1-methylvinyl) pyrrolidone, N-vinyl-5-methyl pyrrolidone, N-vinyl-3, 3-dimethylpyrrolidone, N-vinyl-5-ethyl pyrrolidone, etc.

Dihydrocarbyl dithiophosphate metal salts are frequently used as anti-wear agents and also provide anti-oxidant activity. The zinc salts are most commonly used in lubricating oil in amounts of 0.1 to 10, preferably 0.2 to 2 wt. %, based upon the total weight of the lubricating oil composition. They may be prepared in accord-

ance with known techniques by first forming a dithiophosphoric acid, usually by reaction of an alcohol or a phenol with P_2S_6 and then neutralizing the dithiophosphoric acid with a suitable zinc compound.

Mixtures of alcohols may be used including mixtures of primary and secondary alcohols, secondary generally for imparting improved anti-wear properties, with primary giving improved thermal stability properties. Mixtures of the two are particularly useful. In general, any basic or neutral zinc compound could be used but the oxides, hydroxides and carbonates are most generally employed. Commercial additives frequently contain an excess of zinc due to use of an excess of the basic zinc compound in the neutralization reaction.

The zinc dihydrocarbyl dithiophosphates useful in the present invention are oil soluble salts of dihydrocarbyl esters of dithiophosphoric acid and may be represented by the following formula :



wherein R and R' may be the same or different hydrocarbyl radicals containing from 1 to 18, preferably 2 to 12 carbon atoms and including radicals such as alkyl, alkenyl, aryl, aralkyl, alkaryl and cycloaliphatic radicals. Particularly preferred as R and R' groups are alkyl groups of 2 to 8 carbon atoms. Thus, the radicals may, for example, be ethyl, n-propyl, i-propyl, n-butyl, i-butyl, sec-butyl, amyl, n-hexyl, i-hexyl, n-octyl, decyl, dodecyl, octadecyl, 2-ethylhexyl, phenyl, butylphenyl, cyclohexyl, methylcyclopentyl, propenyl, butenyl etc. In order to obtain oil solubility, the total number of carbon atoms (i.e., R and R' in formula XVI) in the dithiophosphoric acid will generally be about 5 or greater.

The antioxidants useful in this invention include oil soluble copper compounds. The copper may be blended into the oil as any suitable oil soluble copper compound. By oil soluble we mean the compound is oil soluble under normal blending conditions in the oil or additive package. The copper compound may be in the cuprous or cupric form. The copper may be in the form of the copper dihydrocarbyl thio- or dithio-phosphates wherein copper may be substituted for zinc in the compounds and reactions described above although one mole of cuprous or cupric oxide may be reacted with one or two moles of the dithiophosphoric acid, respectively. Alternatively the copper may be added as the copper salt of a synthetic or natural carboxylic acid. Examples include C_{10} to C_{18} fatty acids such as stearic or palmitic, but unsaturated acids such as oleic or branched carboxylic acids such as naphthenic acid of molecular weight from 200 to 500 or synthetic carboxylic acids are preferred because of the improved handling and solubility properties of the resulting copper carboxylates. Also useful are oil soluble copper dithiocarbamates of the general formula $(\text{RR}'\text{NCSS})_n\text{Cu}$, where n is 1 or 2 and R and R' are the same or different hydrocarbyl radicals containing from 1 to 18 and preferably 2 to 12 carbon atoms and including radicals such as alkyl, alkenyl, aryl, aralkyl, alkaryl and cycloaliphatic radicals. Particularly preferred as R and R' groups are alkyl groups of 2 to 8 carbon atoms. Thus, the radicals may, for example, be ethyl, n-propyl, i-propyl, n-butyl, i-butyl, sec-butyl, amyl, n-hexyl, i-hexyl, n-heptyl, n-octyl, decyl, dodecyl, octadecyl, 2-ethylhexyl, phenyl, butylphenyl, cyclohexyl, methylcyclopentyl, propenyl, butenyl, etc. In order to obtain oil solubility, the total number of carbon atoms (i.e., R and R') will generally be about 5 or greater. Copper sulphates, phenates, and acetylacetonates may also be used.

Exemplary of useful copper compounds are copper (Cu^I and/or Cu^{II}) salts of alkenyl succinic acids or anhydrides. The salts themselves may be basic, neutral or acidic. They may be formed by reacting (a) any of the materials discussed above in the Ashless Dispersant section, which have at least one free carboxylic acid (or anhydride) group with (b) a reactive metal compound. Suitable acid (or anhydride) reactive metal compounds include those such as cupric or cuprous hydroxides, oxides, acetates, borates, and carbonates or basic copper carbonate.

Examples of the metal salts of this invention are Cu salts of polyisobutenyl succinic anhydride (hereinafter referred to as Cu-PIBSA), and Cu salts of polyisobutenyl succinic acid. Preferably, the selected metal employed is its divalent form, e.g., Cu^{+2} . The preferred substrates are polyalkenyl succinic acids in which the alkenyl group has a molecular weight greater than about 700. The alkenyl group desirably has a M_n from about 900 to 1400, and up to 2500, with a M_n of about 950 being most preferred. Especially preferred, of those listed above in the section on Dispersants, is polyisobutenyl succinic acid (PIBSA). These materials may desirably be dissolved in a solvent, such as a mineral oil, and heated in the presence of a water solution (or slurry) of the metal bearing material. Heating may take place between 70° and about 200°C . Temperatures of 110° to 140°C are entirely adequate. It may be necessary, depending upon the salt produced, not to allow the reaction to remain at a temperature above about 140°C for an extended period of time, e.g., longer than 5 hours, or decomposition of the salt may occur.

The copper antioxidants (e.g., Cu-PIBSA, Cu-oleate, or mixtures thereof) will be generally employed in an amount of from about 50-500 ppm by weight of the metal, in the final lubricating or fuel composition.

5 The copper antioxidants used in this invention are inexpensive and are effective at low concentrations and therefore do not add substantially to the cost of the product. The results obtained are frequently better than those obtained with previously used antioxidants, which are expensive and used in higher concentrations. In the amounts employed, the copper compounds do not interfere with the performance of other components of the lubricating composition, in many instances, completely satisfactory results are obtained when the copper
10 compound is the sole antioxidant in addition to the ZDDP. The copper compounds can be utilized to replace part or all of the need for supplementary antioxidants. Thus, for particularly severe conditions it may be desirable to include a supplementary, conventional antioxidant. However, the amounts of supplementary antioxidant required are small, far less than the amount required in the absence of the copper compound.

While any effective amount of the copper antioxidant can be incorporated into the lubricating oil composition, it is contemplated that such effective amounts be sufficient to provide said lube oil composition with an amount of the copper antioxidant of from about 5 to 500 (more preferably 10 to 200, still more preferably 10 to 180, and most preferably 20 to 130 (e.g., 90 to 120)) part per million of added copper based on the weight of the lubricating oil composition. Of course, the preferred amount may depend amongst other factors on the quality of the basestock lubricating oil.

20 Corrosion inhibitors, also known as anti-corrosive agents, reduce the degradation of the metallic parts contacted by the lubricating oil composition. Illustrative of corrosion inhibitors are phosphosulfurized hydrocarbons and the products obtained by reaction of a phosphosulfurized hydrocarbon with an alkaline earth metal oxide or hydroxide, preferably in the presence of an alkylated phenol or of an alkylphenol thioester, and also preferably in the presence of carbon dioxide. Phosphosulfurized hydrocarbons are prepared by reacting a suitable hydrocarbon such as a terpene, a heavy petroleum fraction of a C₂ to C₆ olefin polymer such as polyisobutylene,
25 with from 5 to 30 weight percent of a sulfide of phosphorus for 1/2 to 15 hours, at a temperature in the range of 65° to 315°C. Neutralization of the phosphosulfurized hydrocarbon may be effected in the manner taught in U.S. Patent No. 1,969,324.

Oxidation inhibitors reduce the tendency of mineral oils to deteriorate in service which deterioration can be evidenced by the products of oxidation such as sludge and varnish-like deposits on the metal surfaces and
30 by viscosity growth. Such oxidation inhibitors include alkaline earth metal salts of alkylphenolthioesters having preferably C₅ to C₁₂ alkyl side chains, calcium nonylphenol sulfide, barium t-octylphenyl sulfide, dioctylphenylamine, phenylalphanaphthylamine, phosphosulfurized or sulfurized hydrocarbons, etc.

Friction modifiers serve to impart the proper friction characteristics to lubricating oil compositions such as automatic transmission fluids.
35

Representative examples of suitable friction modifiers are found in U.S. Patent No. 3,933,659 which discloses fatty acid esters and amides; U.S. Patent No. 4,176,074 which describes molybdenum complexes of polyisobutenyl succinic anhydride-amino alkanols; U.S. Patent No. 4,105,571 which discloses glycerol esters of dimerized fatty acids; U.S. Patent No. 3,779,928 which discloses alkane phosphonic acid salts; U.S. Patent
40 No. 3,778,375 which discloses reaction products of a phosphonate with an oleamide; U.S. Patent No. 3,852,205 which discloses S-carboxy-alkylene hydrocarbyl succinimide, S-carboxyalkylene hydrocarbyl succinamic acid and mixtures thereof; U.S. Patent No. 3,879,306 which discloses N-(hydroxyalkyl) alkenyl-succinamic acids or succinimides; U.S. Patent No. 3,932,290 which discloses reaction products of di-(lower alkyl) phosphites and epoxides; and U.S. Patent No. 4,028,258 which discloses the alkylene oxide adduct of phosphosulfurized N-(hydroxyalkyl) alkenyl succinimides. The disclosures of the above references are herein incorporated
45 by reference. The most preferred friction modifiers are glycerol mono and dioleates, and succinate esters, or metal salts thereof, of hydrocarbyl substituted succinic acids or anhydrides and thioisobutyl alkanols such as described in U.S. Patent No. 4,344,853.

Pour point depressants lower the temperature at which the fluid will flow or can be poured. Such depressants are well known. Typical of those additives which usefully optimize the low temperature fluidity of the fluid are C₈-C₁₈ dialkylfumarate vinyl acetate copolymers, polymethacrylates, and wax naphthalene.
50

Foam control can be provided by an antifoamant of the polysiloxane type, e.g. silicone oil and polydimethylsiloxane.

Organic, oil-soluble compounds useful as rust inhibitors in this invention comprise nonionic surfactants such as polyoxyalkylene polyols and esters thereof, and anionic surfactants such as salts of alkyl sulfonic acids.
55 Such anti-rust compounds are known and can be made by conventional means. Nonionic surfactants, useful as anti-rust additives in the oleaginous compositions of this invention, usually owe their surfactant properties to a number of weak stabilizing groups such as ether linkages. Nonionic anti-rust agents containing ether linkages can be made by alkoxyating organic substrates containing active hydrogens with an excess of the lower alkylene oxides (such as ethylene and propylene oxides) until the desired number of alkoxy groups have been

placed in the molecule.

The preferred rust inhibitors are polyoxyalkylene polyols and derivatives thereof. This class of materials are commercially available from various sources : Pluronic Polyols from Wyandotte Chemicals corporation ; Polyglycol 112-2, a liquid triol derived from ethylene oxide and propylene oxide available from Dow Chemical Co. ; and Tergitol, dodecylphenyl or monophenyl polyethylene glycol ethers, and Ucon, polyalkylene glycols and derivatives, both available from Union Carbide Corp. These are but a few of the commercial products suitable as rust inhibitors in the improved composition of the present invention.

In addition to the polyols *per se*, the esters thereof obtained by reacting the polyols with various carboxylic acids are also suitable. Acids useful in preparing these esters are lauric acid, stearic acid, succinic acid, and alkyl- or alkenyl-substituted succinic acids wherein the alkyl- or alkenyl group contains up to about twenty carbon atoms.


The preferred polyols are prepared as block polymers. Thus, a hydroxy-substituted compound, R-(OH)_n (wherein n is 1 to 6, and R is the residue of a mono- or polyhydric alcohol, phenol, naphthol, etc.) is reacted with propylene oxide to form a hydrophobic base. This base is then reacted with ethylene oxide to provide a hydrophylic portion resulting in a molecule having both hydrophobic and hydrophylic portions. The relative sizes of these portions can be adjusted by regulating the ratio of reactants, time of reaction, etc., as is obvious to those skilled in the art. Thus it is within the skill of the art to prepare polyols whose molecules are characterized by hydrophobic and hydrophylic moieties which are present in a ratio rendering rust inhibitors suitable for use in any lubricant composition regardless of differences in the base oils and the presence of other additives.

If more oil-solubility is needed in a given lubricating composition, the hydrophobic portion can be increased and/or the hydrophylic portion decreased. If greater oil-in-water emulsion breaking ability is required, the hydrophylic and/or hydrophobic portions can be adjusted to accomplish this.

Compounds illustrative of R-(OH)_n include alkylene polyols such as the alkylene glycols, alkylene triols, alkylene tetrols, etc., such as ethylene glycol, propylene glycol, glycerol, pentaerythritol, sorbitol, mannitol, and the like. Aromatic hydroxy compounds such as alkylated mono- and polyhydric phenols and naphthols can also be used, e.g., heptylphenol, dodecylphenol, etc.


Other suitable demulsifiers include the esters disclosed in U.S. Patents 3,098,827 and 2,674,619.

The liquid polyols available from Wyandotte Chemical co. under the name Pluronic Polyols and other similar polyols are particularly well suited as rust inhibitors. These Pluronic Polyols correspond to the formula :



35

wherein x, y, and z are integers greater than 1 such that the —CH₂CH₂O— groups comprise from about 10% to about 40% by weight of the total molecular weight of the glycol, the average molecule weight of said glycol being from about 1000 to about 5000. These products are prepared by first condensing propylene oxide with propylene glycol to produce the hydrophobic base



45

This condensation product is then treated with ethylene oxide to add hydrophylic portions to both ends of the molecule. For best results, the ethylene oxide units should comprise from about 10 to about 40% by weight of the molecule. Those products wherein the molecular weight of the polyol is from about 2500 to 4500 and the ethylene oxide units comprise from about 10% to about 15% by weight of the molecule are particularly suitable.

The polyols having a molecular weight of about 4000 with about 10% attributable to (CH₂CH₂O) units are particularly good. Also useful are alkoxyfatty amines, amides, alcohols and the like, including such alkoxyfatty acid derivatives treated with C₉ to C₁₈ alkyl-substituted phenols (such as the mono- and di-heptyl, octyl, nonyl, decyl, undecyl, dodecyl and tridecyl phenols), as described in U.S. Patent 3,849,501, which is also hereby incorporated by reference in its entirety.

These compositions of our invention may also contain other additives such as those previously described, and other metal containing additives, for example, those containing barium and sodium.

The lubricating composition of the present invention may also include copper lead bearing corrosion inhibitors. Typically such compounds are the thiadiazole polysulphides containing from 5 to 50 carbon atoms, their derivatives and polymers thereof. Preferred materials are the derivatives of 1,3,4-thiadiazoles such as those described in U.S. Patents 2,719,125 ; 2,719,126 ; and 3,087,932 ; especially preferred is the compound 2,5

5 bis (t-octadithio)-1,3,4-thiadiazole commercially available as Amoco 150. Other similar materials also suitable are described in U.S. Patents 3,821,236 ; 3,904,537 ; 4,097,387 ; 4,107,059 ; 4,136,043 ; 4,188,299 ; and 4,193,882.

Other suitable additives are the thio and polythio sulphenamides of thiadiazoles such as those described in U.K. Patent Specification 1,560,830. When these compounds are included in the lubricating composition, we prefer that they be present in an amount from 0.01 to 10, preferably 0.1 to 5.0 weight percent based on the weight of the composition.

10 Some of these numerous additives can provide a multiplicity of effects, e.g. a dispersant-oxidation inhibitor. This approach is well known and need not be further elaborated herein.

Compositions when containing these conventional additives are typically blended into the base oil in amounts effective to provide their normal attendant function. Representative effective amounts of such additives (as the respective active ingredients) in the fully formulated oil are illustrated as follows :

15

<u>Compositions</u>	<u>Wt. % A.I.</u> <u>(Preferred)</u>	<u>Wt. % A.I.</u> <u>(Broad)</u>
Viscosity Modifier	0.01-4	0.01-12
20 Detergents	0.01-3	0.01-20
Corrosion Inhibitor	0.01-1.5	.01-5
Oxidation Inhibitor	0.01-1.5	.01-5
25 Dispersant	0.1-8	.1-20
Pour Point Depressant	0.01-1.5	.01-5
Anti-Foaming Agents	0.001-0.15	.001-3
Anti-Wear Agents	0.001-1.5	.001-5
30 Friction Modifiers	0.01-1.5	.01-5
Mineral Oil Base	Balance	Balance

35 When other additives are employed, it may be desirable, although not necessary, to prepare additive concentrates comprising concentrated solutions or dispersions of the novel dispersants of this invention (in concentrate amounts hereinabove described), together with one or more of said other additives (said concentrate when constituting an additive mixture being referred to herein as an additive-package) whereby several additives can be added simultaneously to the base oil to form the lubricating oil composition. Dissolution of the additive concentrate into the lubricating oil may be facilitated by solvents and by mixing accompanied with mild heating, but this is not essential. The concentrate or additive-package will typically be formulated to contain 40 the additives in proper amounts to provide the desired concentration in the final formulation when the additive-package is combined with a predetermined amount of base lubricant. Thus, the dispersants of the present invention can be added to small amounts of base oil or other compatible solvents along with other desirable additives to form additive-packages containing active ingredients in collective amounts of typically from about 45 2.5 to about 90%, and preferably from about 15 to about 75%, and most preferably from about 25 to about 60% by weight additives in the appropriate proportions with the remainder being base oil.

The final formulations may employ typically about 10 wt. % of the additive-package with the remainder being base oil.

50 All of said weight percents expressed herein (unless otherwise indicated) are based on active ingredient (A.I.) content of the additive, and/or upon the total weight of any additive-package, or formulation which will be the sum of the A.I. weight of each additive plus the weight of total oil or diluent.

This invention will be further understood by reference to the following examples, wherein all parts are parts by weight, unless otherwise noted and which include preferred embodiments of the invention.

55 EXAMPLE 1 - PREPARATION OF ETHYLENE PROPYLENE COPOLYMER

A 1 liter Zipperclave reactor (Autoclave Engineers) equipped with a water jacket for temperature control, with a septum inlet for syringe injection of catalyst, and with a supply of purified nitrogen, liquid propylene, and ethylene was used in these polymerizations. The reactor was cleaned with hot toluene and then was purged well with dry nitrogen at 100°C. The reactor was cooled to 25°C and 10.0 cc of a 4.0 wt% toluene solution

of methylalumoxane was injected along with 100 cc of distilled toluene at 0 psig under nitrogen. Liquid propylene monomer (200 cc) was added from a calibrated burette at 25°C. The reactor contents were stirred and heated to 115°C at which point the reactor pressure was 375 psig. 1.00 cc of a toluene solution of bis(n-butylcyclopentadienyl) zirconium dichloride (1.00 mg) was injected and ethylene at a pressure of 405 psig was immediately supplied. Ethylene was fed on pressure demand in order to keep the system pressure at 405 psig. The rate of ethylene flow was recorded continuously during the course of the polymerization. The reaction was continued for 15 minutes after which the reaction was stopped by rapidly depressuring and cooling the reactor to 25°C. The polymer product was collected and the toluene solvent was evaporated in an air stream. The polymer weight was determined to be 103.1 gms, and the polymer was analyzed by size-exclusion chromatography and found to have a number average molecular weight of 1100, a weight average molecular weight of 5400 and a polydispersity of 4.9. The polymer product was found to contain 2.5 ppm Zr and 1.75 ppm Cl.

15 EXAMPLE 2 - ALKYLATION OF PHENOL

About 50 g. of the ethylene-propylene copolymer produced in Example 1 was dissolved in 100 ml of chlorobenzene and added to a solution containing 10.45 g. of phenol in 300 ml of chlorobenzene. While stirring at room temperature under a nitrogen blanket, 0.5 g. of BF_3 gas was bubbled into the charged solution, and the reaction mixture was stirred while the temperature was increased to 50°C for about 1 hour. The reaction mixture was then neutralized with gaseous ammonia until a neutral pH was obtained. The solution was filtered and the filtrate was heated to 150°C to distill off the solvent and excess phenol. Analytical results showed 91.4 % conversion to the desired ethylene-propylene copolymer substituted phenol. No trace of double bond peak at 890 cm^{-1} was found in the infra-red analysis of the alkylated phenol product so produced.

25 EXAMPLE 3 - MANNICH BASE CONDENSATION

25 Grams of the alkylated phenol prepared as in Example 2 is dissolved in 25 g. of S150N lubricating oil. To the solution is added 0.61 g. of 1,6-hexanediamine and 0.35 g. of formaldehyde at 30°C under N_2 . The mixture was heated to 115°C and kept at that temperature for 1 hour in a four necked round bottomed 500 ml flask. Then, the reaction mixture's temperature was raised to 130°C while the reaction vessel was swept with dry N_2 gas for 45 minutes. The stripped reaction mixture was then cooled to room temperature, diluted with 100 ml. of heptane, and filtered. The filtrate was then stripped at 130°C with dry N_2 gas to remove heptane. The resulting Mannich base condensation product was evaluated to determine its dispersancy properties and its viscometric properties.

The product mixture of Example 3 was determined to have a kinematic viscosity of 6.4 cSt (at 100°C, ASTM Method D445) and a CCS viscosity of 23.39 (at -20°C, ASTM Method D2602), thereby providing a VR value of about 3.6, as compared to the S150N oil itself which has a KV of 5.2 cSt and a CCS viscosity of 19.2 cSt, or a VR of 3.7.

The dispersancy of the thus-prepared product is tested for sludge inhibition (via the SIB test) and varnish inhibition (via the VIB test). The SIB test has been found, after a large number of evaluations, to be an excellent test for assessing the dispersing power of lubricating oil dispersant additives.

The medium chosen for the SIB test is a used crankcase mineral lubricating oil composition having an original viscosity of about 325 SUS at 38°C that had been used in a taxicab that is driven generally for short trips only, thereby causing a buildup of a high concentration of sludge precursors. The oil that is used contains only a refined base mineral lubricating oil, a viscosity index improver, a pour point depressant and zinc dialkyldithiophosphate anti-wear additive. The oil contains no sludge dispersant. A quantity of such used oil is acquired by draining and refilling the taxicab crankcase at 1000 - 2000 mile intervals.

The SIB test is conducted in the following manner: the aforesaid used crankcase oil, which is milky brown in color, is freed of sludge by centrifuging for one hour at about 39,000 gravities (gs.). The resulting clear bright red supernatant oil is then decanted from the insoluble sludge particles thereby separated out. However, the supernatant oil still contains oil-soluble sludge precursors which on heating under the conditions employed by this test will tend to form additional oil-insoluble deposits of sludge. The sludge inhibiting properties of the additives being tested are determined by adding to portions of the supernatant used oil, a small amount, such as 0.5, 1 or 2 weight percent, of the particular additive being tested. Ten grams of each blend being tested are placed in a stainless steel centrifuge tube and are heated at 135°C for 16 hours in the presence of air. Following the heating, the tube containing the oil being tested is cooled and then centrifuged for about 30 minutes at room temperature at about 39,000 gs. Any deposits of new sludge that form in this step are separated from the oil by decanting the supernatant oil and then carefully washing the sludge deposits with 25 ml of heptane to remove all remaining oil from the sludge and further centrifuging. The weight of the new solid sludge that has been for-

med in the test, in milligrams, is determined by drying the residue and weighing it. The results are reported as amount of precipitated sludge in comparison with the precipitated sludge of a blank not containing any additional additive, which blank is normalized to a rating of 10. The less new sludge precipitated in the presence of the additive, the lower the SIB value and the more effective is the additive as a sludge dispersant. In other words, if the additive gives half as much precipitated sludge as the blank, then it would be rated 5.0 since the blank will be normalized to 10.

The VIB test is used to determine varnish inhibition. Here, the test sample consists of 10 grams of lubricating oil containing a small amount of the additive being tested. The test oil to which the additive is admixed is of the same type as used in the above-described SIB test. The ten gram sample is heat soaked overnight at about 140°C and thereafter centrifuged to remove the sludge. The supernatant fluid of the sample is subjected to heat cycling from about 150°C to room temperature over a period of 3.5 hours at a frequency of about 2 cycles per minute. During the heating phase, gas which was a mixture of about 0.7 volume percent SO₂, 1.4 volume percent NO and balance air is bubbled through the test sample. During the cooling phase, water vapor is bubbled through the test sample. At the end of the test period, which testing cycle can be repeated as necessary to determine the inhibiting effect of any additive, the wall surfaces of the test flask in which the sample is contained are visually evaluated as to the varnish inhibition. The amount of varnish imposed on the walls is rated to values of from 1 to 11 with the higher number being the greater amount of varnish, in comparison with a blank with no additive that was rated 11.

10.00 grams of SIB test oil are mixed with 0.05 grams of the product of Example 2 and tested in the aforescribed SIB and VIB tests.

The dispersant material of Example 3 provided a SIB rating of 6.0, and a VIB rating of 2.5, indicating the presence of dispersant properties.

The principles, preferred embodiments, and modes of operation of the present invention have been described in the foregoing specification. The invention which is intended to be protected herein, however, is not to be construed as limited to the particular forms disclosed, since these are to be regarded as illustrative rather than restrictive. Variations and changes may be made by those skilled in the art without departing from the spirit of the invention.

Claims

1. A lubricating oil dispersant additive useful in oleaginous compositions which comprises a condensation product obtained by the reaction of :
 - (a) at least one alkyl-substituted hydroxyaromatic compound formed by the alkylation of at least one hydroxy aromatic compound with at least one terminally unsaturated ethylene alpha-olefin polymer of 300 to 20,000 number average molecular weight, at least 30% of said polymer's chains contain terminal ethenylidene unsaturation ;
 - (b) at least one aldehyde reactant ; and
 - (c) at least one nucleophilic reactant.
2. The dispersant additive of claim 1 wherein said polymer comprises an ethylene-propylene copolymer.
3. The dispersant additive of claim 1 wherein said alpha-olefin comprises butene-1.
4. The dispersant additive of any of claims 1 to 3 wherein said copolymer has a number average molecular weight of from 700 to 15,000.
5. The dispersant additive of claim 4 wherein said number average molecular weight is from 1,500 to 5,000.
6. The dispersant additive of any of claims 1 to 5 wherein said polymer has a molar ethylene content of from 20 to 80 percent.
7. The dispersant additive of claim 6 wherein said polymer has a molar ethylene content of from 45 to 65 percent.
8. The dispersant additive according to any of claims 1 to 7 wherein the nucleophilic reagent comprises an amine containing from 2 to 60 carbon atoms and from 1 to 12 nitrogen atoms per molecule.

- 5 9. The dispersant additive according to claim 8 wherein said amine comprises a polyalkylenepolyamine wherein said alkylene group contains 2 to 60 carbons and said polyalkylenepolyamine contains from 2 to 9 nitrogen atoms per molecule.
10. The dispersant additive according to claim 9 wherein said amine comprises polyethylenepolyamine.
- 10 11. The dispersant additive according to any of claims 1 to 10 which is borated to provide from 0.05 to 2.0 weight percent boron in said borated dispersant additive.
12. A concentrate containing from 3 to 45 weight percent of the dispersant additive of any of claims 1 to 11.
13. A concentrate as claimed in claim 12 containing from 10 to 35 weight percent of the dispersant additive.
- 15 14. A lubricating oil composition containing from 0.1 to 20 weight percent of the dispersant additive of any of claims 1 to 11.
- 20 15. An aromatic compound having improved viscosity properties which comprises alkyl-substituted hydroxyaromatic compounds formed by the alkylation of at least one hydroxy aromatic compound with an ethylene alpha-olefin polymer of 300 to 20,000 number average molecular weight, wherein at least 30% of said polymer's chains contain terminal ethenylidene unsaturation.
- 25 16. The aromatic compound of claim 15 wherein said polymer is as defined in any of claims 2 to 7.
17. The aromatic compound of claim 15 or claim 16 wherein said polymer has a VR value of less than 4.1.
- 30 18. A process for producing a low sediment lubricating oil dispersant material which comprises contacting (A) at least one alkyl-substituted hydroxyaromatic compound as claimed in claim 15 or claim 16 (B) at least one aldehyde reactant ; and (C) at least one nucleophilic reactant, under condensation conditions to form said dispersant material characterized by a VR' value of less than 4.1.

35

40

45

50

55